| No. | Status | Date |
|---|---|---|
| LNDE-RPT-96-014-DFR-3 | Issued | 1996-03-08 |

# Daily Field Report 3 - Baseline Ultrasonic Thickness Survey - ATU-100

## Scope and Responsibilities

Grace Okafor performed a baseline ultrasonic thickness survey on specified piping within the ATU-100. The objective was to establish initial thickness measurements for asset integrity monitoring prior to startup.

All activities were conducted in accordance with the requirements of QSCP-NDT-001 Rev 0. Work was performed under the authorization of the cold work permit QSCP-WP-1996-00412.

## Equipment and Calibration

Thickness measurements were acquired using a Panametrics 26DL PLUS 9411820. The instrument's validity was verified against LNDE-CAL-1996-0031.

Field calibration and verification were performed using LNDE-CS-001. All measurement procedures adhered to the guidelines set forth in ASTM E797.

## Inspection Results - Process Piping

Thickness readings were taken on 2-RF-102 (A312 TP316, OD 60.3 mm) and 4-LA-104 (A106 Gr.B, OD 114.3 mm). The survey focused on verifying the nominal thicknesses of 3.91 mm and 6.02 mm respectively against their minimums.

Measurements were also recorded for 4-RA-104 (A106 Gr.B, OD 114.3 mm), noting the nominal thickness of 8.56 mm. All readings for these lines were found to be above the specified t-min values.

## Inspection Results - Utility Piping

The survey included 2-ST-101 (A106 Gr.B, OD 60.3 mm) with a nominal thickness of 3.91 mm. The measured values were compared to the retirement thickness of 2.29 mm.

Baseline readings were completed for the cooling water lines 3-CW-101 and 3-CW-102 (A106 Gr.B, OD 88.9 mm). Both lines exhibited a nominal thickness of 5.49 mm, exceeding the t-min of 2.79 mm.

| Sign-off | Name | Function | Date | Signature |
|---|---|---|---|---|
| Prepared | Grace Okafor | UT technician, SNT-TC-1A UT Level II | 1996-03-08 | _____ |