DEMO SYNTHETIC CEMENTING INCIDENT REPORT

Well: SYN-WELL-A04
Date: 2024-07-18
MD: 1850.0 m | TVD: 1820.0 m
Formation: SYN-FM-BRAVO
Event: cementing_channel / channeling / poor bond
NPT: 16.5 hours

Summary: Micro-annular gas channeling detected after 9-5/8 inch casing cement job.
Mitigation: Performed remedial squeeze cementing with micro-fine cement slurry.
Outcome: Isolation verified via CBL-VDL log with 95% bond index.
Lesson learned: Centralize casing at 15m intervals across porous Bravo zones.