

	<i>aluminum bd.</i>	<i>outer pigskin</i>	<i>back pigskin</i>	<i>cork</i>	<i>denim</i>	<i>rubber bd.</i>	<i>Japanese paper</i>	<i>wood bd.</i>
aluminum bd.	95.0	0.0	0.0	0.0	0.0	5.0	0.0	0.0
outer pigskin	4.0	57.0	7.0	0.0	2.0	5.0	1.0	24.0
back pigskin	1.0	14.0	59.0	1.0	2.0	6.0	0.0	17.0
cork	1.0	4.0	7.0	77.0	2.0	1.0	0.0	8.0
denim	0.0	8.0	3.0	0.0	85.0	1.0	1.0	2.0
rubber bd.	38.0	0.0	0.0	0.0	0.0	55.0	0.0	7.0
Japanese paper	0.0	0.0	1.0	0.0	0.0	5.0	93.0	1.0
wood bd.	17.0	2.0	4.0	0.0	0.0	33.0	0.0	44.0