

8000 Neutral Silicone Sealant

FEATURES

- Good extrusion and thixotropy between 4℃~+40℃.
- Neutral curing, non-corrosive curing system
- No unpleasant odor during curing
- Excellent resistance to weather, UV, ozone, water
- Good adhesion to most common building material
- Good compatibility with other neutral silicone sealants

COMPOSITION

- One-part, neutral-curing
- RTV silicone sealant

APPLICATIONS

- Sealing gaps or joints of doors and windows
- Many other uses

TYPICAL PROPERTIES

Property	Result
Uncured-As Tested at 23°C (73°F) and 50% RH	
Specific Gravity	1.5g/cm ³
Tack-free time(23°C/73°F, 50% RH)	10-15 minutes
Curing time(23°C/73°F, 50% RH)	≥2.0 mm/24h
Flow, Sag or Slump	<0.1mm
VOC Content	<39g/L
Extrudability	≥120g/min
As Cured-After 21 days at 23°C (73°F) and 50% RH	
Durometer Hardness, Shore A	40-45
Joint Movement Capability	± 20%
Tensile Adhesion Strength	>0.7Mpa
Elongation	>350%
AT 50% elongation	0.268MPa

DESCRIPTION

8000 Neutral Silicone Sealant is one-component, neutral curing, general purpose construction silicone sealant with good adhesion to glass, aluminum, cement, concrete etc., specially designed for sealing in all type door ,window and wall joints

SPECIFICATIONS

8000 Neutral Silicone Sealant meets or exceeds the requirements of the following

standards for one-part sealants.

COLORS

Available in black, gray and white and translucent color(standard colors)

Available in other wide variety of colors (customized)

PACKAGING

8000 Neutral Silicone Sealant is available in 300 ml plastic caulking cartridges and 600 ml foil sausage packs

USABLE LIFE AND STORAGE

When stored at or below 27°C (80°F) in the original unopened containers, 8000 Neutral Silicone Sealant has a usable life of 12 months from the date of manufacture.

LIMITATIONS

8000 Neutral Silicone Sealant should not be used, applied or recommended:

- In structural glazing applications or where the sealant is intended as an adhesive.
- In areas where abrasion and physical abuse are encountered.
- In totally confined spaces as the sealant requires atmospheric moisture for cure.
- On frost-laden or damp surfaces
- To building materials that bleed oils, plasticizers or solvents – materials such as impregnated wood, oil-based caulks, green or partially vulcanized rubber gaskets or tapes.
- In below-grade applications
- On substrates made of PP, PE, PC, PMMA and PTFE.
- Where movement capability greater than $\pm 20\%$ is required.
- Where painting of the sealant is required, as the paint film may crack and peel
- For structural adhesion on bare metals or surfaces subject to corrosion (i.e., mill aluminum, bare steel, etc.)
- To surfaces in contact with food
- For use underwater or in other applications where the product will be in continuous contact with water.
- New concrete must be allowed to cure and dry for at least 7 days of good drying weather.

HANDLING AND SAFETY

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE FROM JIAOZHIBAO SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING BAIYUN



Guangdong Jiaozhibao New Materials Technology Co., Ltd.
Address: No. 37 Deye Road, Yinghong Town, Yingde City, Guangdong Province, China
Contact: 15920132200 E-mail: 3862617819@qq.com

CUSTOMER SERVICE.

HOW TO USE

Complete design and installation guidelines are contained in the JIAOZHIBAO Technical Manual when using this product.

HEALTH AND ENVIRONMENT INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Material Safety Data Sheets containing physical, ecological toxicological and other safety-related data.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of using our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that the products of Guangdong Jiaozhibao New Materials Technology Co., Ltd. are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

The warranty of Guangdong Jiaozhibao New Materials Technology Co., Ltd. is that the product will meet the Guangdong Jiaozhibao New Materials Technology Co., Ltd. sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchasing price or replacement of any product shown to be other than as warranted.

GUANGDONG JIAOZHIBAO NEW MATERIALS TECHNOLOGY CO.,LTD SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

GUANGDONG JIAOZHIBAO NEW MATERIALS TECHNOLOGY CO.,LTD DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.