

D5-AQUASTOP

UNIVERSAL DRY WATERPROOF MIXTURE

FOR REPAIR AND PROTECTION OF CONCRETE, REINFORCED CONCRETE AND STONE STRUCTURES

Complies with State Standards GOST P 56378-2015 and GOST 33083-2014

DESCRIPTION

Dry building mix based on high-strength cement, fine-grained quartz sand, innovative admixture D5, polypropylene fiber and specially selected modifying admixtures, which increase adhesion and compensate for shrinkage. When mixed with water the material forms a plastic thixotropic composition with high adhesion to concrete and metal. It prevents corrosion in reinforcing steel.

PROPERTIES

- high water-resistance;
- accelerated strength gain and water-resistance gain;
- high plasticity;
- high frost-resistance;
- vapor-permeable;
- antifungal;
- eco-friendly, approved for using in drinking water tanks, swimming pools and fish-breeding pools;
- for horizontal, vertical and ceiling surfaces;
- increased strength and durability;
- works both on positive and negative effects of water pressure;
- high sulfate-resistance;
- high adhesion;
- chemical-resistant;
- for manual and mechanised application;
- does not contain chlorides and other substances which can cause reinforcement corrosion.

APPLICATION AREA

Universal waterproof mixture **D5-AQUASTOP** is designed for repair and waterproofing of concrete, reinforced concrete and stone structures, including:

- repair and waterproofing of hydraulic structures, tunnels, bridges, ports and reclamation constructions, foundations, basements, swimming pools, fountains, drinking water tanks, treatment facilities and other structures contacting water;
- repair of runways of airfields;
- repair of concrete and reinforced concrete structures, including repair of chips, potholes, cavities, as well as restoring of protective layer of concrete;
- sealing of field welds and holes in concrete from formwork studs;
- water-resistant protection of structures operated in aggressive environment: sea water, domestic sewage drains, waste water with oil products, liquid waste from animal husbandry and poultry farming and others;
- external and internal waterproofing of buildings and structures of concrete, reinforced concrete and stone;
- plastering of facades and plinths;
- plastering of bathrooms, toilets, baths, saunas and other rooms with increased humidity to eliminate dampness and mold.

HS CODE: 3824 50 900 0

FOUNDATION PREPARATION

Foundation should be cleaned from dust, loose and fragile areas and abundantly watered. Plastering can be started after water is completely absorbed. Under high negative water pressure, it is necessary to attach a galvanized mesh to the wall to prevent the plastering layer from tearing off the foundation. In other cases, there is no need to use a mesh, because the fiber in **D5-AQUASTOP** plays the role of three-dimensional reinforcement.

WORK EXECUTION

The dry mix **D5-AQUASTOP** (25 kg) is mixed with 4.5 to 5.0 liters of water (different cements have different water consumption) in a container with a construction mixer at a speed of about 500 rpm until a homogeneous mixture is obtained. The ready-made mixture should be used within 45-60 minutes from the moment of mixing with water.

The ready-made mixture is applied to the foundation with a trowel or spatula or mechanically. If the plastering layer is thick, the mixture is applied in several steps without levelling the previous layer. In this case every subsequent layer is applied after the previous layer had dried and had gained the needed strength. The last layer is levelled with a rod until a smooth surface is obtained.

If the mixture is applied mechanically, it is necessary to adjust the dosage of water to obtain the required consistency of the plaster mix. The mixture is applied with a spray gun to the prepared foundation with a thickness of 5-20 mm, then it is levelled with a rod until a smooth surface is obtained. When the mixture begins to set, the surface is watered and rubbed with a grater.

The plastered surface must be moistened during the first 5-7 days, and the facade plaster must be moreover protected from direct sunlight during the same period in order to prevent cracks. If cracks appear, they must be watered abundantly and rubbed with a freshly-made **D5-AQUASTOP** mix.

RECOMMENDATIONS

Works should be carried out at temperatures from +5°C to +40°C.

The plaster layer 10 mm thick can withstand hydrostatic loads on the 5-7 day.

Tiling can be done in 5-7 days.

SHELF LIFE AND PACKAGING

The mix is supplied in 25 kg multilayer bags.

Shelf life when stored on pallets in undamaged packaging is 12 months.

SPECIFICATIONS

D5-AQUASTOP mix composition	Cement, quartz sand, admixture D5, modifying admixtures, alkali-resistant fiber
Color	gray
Bulk density	1.5-1,6 t / m ³
Quantity of mixing water	4,5-5,0 liters per 25 kg of mix
Mixture consumption with the application layer: - of 10 mm thick - of 5 mm thick	- 10 kg / m ² - 5 kg / m ²
Maximum particle size	0.315 mm
Compressive strength	no less than 30 MPa
Flexural tensile strength	no less than 5 MPa
Adhesion to foundation	no less than 1,5 MPa
Frost-resistance	no less than F 400
Water-resistance of the plaster layer	no less than 1,4 MPa (W 14)
Operating temperature	from -50°C to +70°C

MANUFACTURER: SPE TOKAR Co., Ltd, 19 A, Pozharskogo Str., 362002, Vladikavkaz, Russia

Tel: +7 (918) 823-08-05, +7 (938) 883-10-37; e-mail: info.dobavkad5@mail.ru; www.d5-tokar.ru