					METTALUF	RGICAL TE	T REPORT	T.									
HAPPY FORGINGS LIMITED, LUDHIANA				(FROM SUB CONTRACTOR)  (DOC. NO. FM:HT-LB-11)													
									CUSTOMER N	I/s Ve	Ve Comme. (Dewas)						
									STEEL MILL M/S	S	AARTI STEEL			REPORT NO.			8227
CHALLAN NO.				DATE		05.02.2018											
HEAT NO.		6192		SECTION SIZE		80 DIA											
GRADE		EN-353		NO. OF BAR													
QTY.				LENGTH RANGE		4.5 TO 5.5 MTRS											
PART NO.		77145		COLOUR CODE		BLUE+WHITE BASE											
SPE FORD -		CHEMICA	AL PROPE	RTIES	A.												
	C%	Mn%	Si%	5%	P%	Cr%	Ni%	Mo%									
MIN.		0.50	0.10			0.75	1.00	0.08									
MAX	0.20	1.00	0.35	0.040	0.040	1.25	1.50	0.15									
HFL OBSERVED	0.192	0.92	0.19	0.023	0.013	1.19	1.05	0.126									
		PHYSICA	L PROPE	RTIES													
INTERNAL SOUNDNESS		C2 R1 S1															
GRAIN FLOW																	
SURFACE HARDNESS(BHN)																	
UPSETTING TESTING		ОК															
		METAI	LLOGRAP	HY													
GRAIN SIZE-ASTM E-112				ASTM-	7												
	A	A		В С		D											
NCLUSSION RATING WORST	TK	.TN	TK	TN	TK	TN	TK	TN									
FIELD AS PER ASTM E-45	0.5	1.5	0	0.5	0	0	0	1									
		JOMINY	TRASVE	LET													
DISTT.			J6/16"														
SPEC.			36-40														
HFL OBSERVED HRC			40														
EMARKS MILL T. C. ENCLOSED																	

AUTHORISED SIGNATURY