						The second second			
HAPPY FORGINGS LIMITED, LUDHIANA				(FROM SUB CONTRACTOR)					
CUSTOMER M/s	Ve	Comme. (D	ewas)						
STEEL MILL M/S	Aarti Steel			REPORT NO.		8006			
CHALLAN NO.				DATE		30.01.2018			
HEAT NO.	6045			SECTION SIZE		90 Dia			
GRADE	EN-353			NO. OF BARS/BILLET					
QTY.				LENGTH RANGE		4.5 TO 5.5 MTRS			
PART NO.	5613/5690			COLOUR CODE		BLUE+WHITE BASE			
		CHEMIC	AL PROPER	TIES	ž.				
SPEC.	C%	Mn%	Si%	S%	P%	Cr%	Ni%	Mo%	
MIN.		0.50	0.10			0.75	1.00	0.08	
MAX	0.20	1.00	0.35	0.040	0.040	1.25	1.50	0.15	
HFL OBSERVED	0.173	0.95	0.215	0.026	0.017	1.19	1.07	0.12	
		PHYSIC	AL PROPER	TIES		Z:			
INTERNAL SOUNDNESS	C2 R1 S1								
GRAIN FLOW									
SURFACE HARDNESS(BHN)									
UPSETTING TESTING	ОК								
		META	ALLOGRAPH	IY					
GRAIN SIZE-ASTM E-112				ASTM-7					
	Α .		В .		С		D		
INCLUSSION RATING WORST	TK	TN	TK	TN	TK	TN	TK	TN	
FIELD AS PER ASTM E-45	0.5	1.5	0	0.5	0	0	0	1	
		JOMIN	Y TRASVEL	ET					
DISTT.			J11MM						
SPEC.			38 HRC MIN						
HFL OBSERVED HRC			38			131			
REMARKS	MILL T. C. ENCLOSED					2 - 1			

AUTHORISED SIGNATURY

METTALURGICAL TEST REPORT