

R. L. STEELS & ENERGY LTD. **TEST CERTIFICATE**

Regd. Office: Gut No. 78 to 81, Pangra Shiver Chitegaon, Paithan Road, Aurangabad - 431 107 Maharashtra, India. Phone: 02431-661231, 251163 Fax: 02431-251879 E-mail: qc@rlsteels.com, Website: www.rlsteels.com

Format No. : FT/QAD/03 Issue Dt :01/10/2017 Rev No.: 00

Customer: M/S UNIQUE FORGINGS (INDIA) PVT. LTD.

		IDC, NEAR I			i, VIIIIIAL	001001	VAGAIN, G	jujiat.								
General	Informa	tion & Mat	erial Deta	ils												
TC NO.		Date	Invoid	Invoice No.		Tru	Truck No.		Quantity in MT	Length	Sı	Supply Condition		Colour code		
18-0641 23-05-2018 Process Route		23-05-2018	RL18-SI-0703		23-05-2018	MH 20	BT 2121	208	16.080	5.0 TO 6.0 MTR	AS ROLLED		YELLOW+ BLUE+WHITE			
		Heat No.		Grade EN353		As Cast Size		Prod	uct Size	Reduction Ratio		Customer TDC				
EAF/LRF/VD/CCP-with MEMS								48DIA		15.92:1		· · · · · ·				
Chemica	al Compo	sition & T	ramp Ele	ments												
ent	%C	%Si	%Mn	%P	%S	%Cr	%Ni	%Mo	%Cu	%V	%AI	%Ti	%В	%Ca	%A:	
	-		0.50	1	Y -	0.75	1.00	0.08	-	-		-		-	, -	
lax.	0.20	0.35	1.00	0.050	0.050	1.25	1.50	0.15	-	-	-	-	-	-		
ctual	0.185	0.22	0.94	0.032	0.022	1.04	1.02	0.130		-	0.023	-	-	-	-	
ramp Elements (Contd.) & DI / CE								Gas Analys	sis.		Dimensio		n Tolera	ince		
Element	%Sn	%Pb	%Sb	%Sb CE DI Valu		lue			O2	H2	N2	Size Tol				
Min	-	-	-	-	-		(PPM)	Min	-		-	Specification		As per IS 3739, Grade I.		
Max		-	-	- \			Gas (Max	-	-	-					
Actual -		-	-	-	-			Actual	10.00	1.50	75.00					
/lechani	cal Prop	erties									Macros	structure	Mic	rostru	cture	
est Code	Hardness As Rolled (BHN)	Condition)		g/mm²) UTS (Kg/mm		/mm²)	%EI.	%RA	Impact Val	Impact Values (Joules)		Macrostructure As		-		
		(BHN)							Izod	Charpy	per AS	()				
Spec.	-	-	•		-			-	-	•	-		•			
Actual Value	197-206	-	-			•					C2R1S1					
llurg	gical Pro	perties									Other 7	Test Resu	ılts			
Test Code ·		Decarb ASTM J419 (mm)	Grain Size as per ASTM E112	Inclusion Rating (As per IS 4136			/ ASTME-45A) Plate IR		Magnaflux Test (100%		UT Test	Spark/Spe ctral Test	4			
				Series	Α	В	С	D	Bars)		Bars)	(100% Bars)				
Spec.		-	-	T/H		-	-	-	-		-	-				
Actual Value		-	6.0 / 7.0	T/H	1.5 / 0.5	0.5 / 0.0	0.0 / 0.0	1.5 / 0.5	ок		ОК	ок	-	-		
ardena	bility Tes	t Result														
Jominy Distance mm/inch)	J 6/16"															
Spec (HRC)	36-40															
	-								,				2	(See-		

AUTHORISED SIGNATORY)

DECLARATION: TEST RESULTS ARE BASED ON ACTUAL TESTS CARRIED OUT ON SAMPLES DRAWN AS PER QUALI PLAN. TEST CERTIFICATE CONFORMS TO THE CUSTOMER TDC.