



R. L. STEELS & ENERGY LTD.

TEST CERTIFICATE

Regd. Office: Gut No. 78 to 81, Pangra Shiver Chitegaon, Palthan Road, Aurangabad - 431 107
Maharashtra, India. Phone : 02431-661231, 251163 Fax : 02431-251679
E-mail : qc@rlsteels.com, Website : www.rlsteels.com

Format No. : FT/QAD/03
Issue Dt : 01/10/2017
Rev No. : 00

Customer: M/S HAPPY FORGINGS.LTD.(UNIT II)

B- XXIX-2254/1 & OPP. HINDUSTAN TYRES (ADJ. WARYAM STEELS), KANGANWAL ROAD, PO-JUGIANA, LUDHIANA.

General Information & Material Details

TC NO.	Date	Invoice No.	Date	Truck No.	No. of Pcs	Quantity in MT	Length	Supply Condition	Colour code
18-0180	20-04-2018	RL18-SI-0233	20-04-2018	RJ 50 GA 0529	28	27.350	5.0 to 6.0 MTR	AS ROLLED	YELLOW+ BLUE+WHITE
Process Route		Heat No.	Grade	As Cast Size		Product Size		Reduction Ratio	Customer TDC
EAF/LRFVD/CCP-with MEMS		2-XGJ-4	EN353	280X320		115 DIA		8.63:1	-

Chemical Composition & Tramp Elements

Element	%C	%Si	%Mn	%P	%S	%Cr	%Ni	%Mo	%Cu	%V	%Al	%Ti	%B	%Ca	%As
Min.	0.14	-	0.50	-	0.020	0.75	1.00	0.08	-	-	0.020	-	-	-	-
Max.	0.20	0.35	1.00	0.035	0.040	1.25	1.50	0.15	-	-	0.040	-	-	-	-
Actual	0.19	0.23	0.96	0.020	0.029	1.09	1.03	0.145	-	-	0.028	-	-	-	-

Tramp Elements (Contd.) & DI / CE

Gas Analysis.				Dimension Tolerance			
Element	%Sn	%Pb	%Sb	CE	DI Value	O2	H2
Min	-	-	-	-	-	Min	-
Max	-	-	-	-	-	Max	2.50
Actual	-	-	-	-	-	Actual	1.30

Mechanical Properties

Test Code	Hardness (H&T Condition) (BHN)	YS (Kg/mm ²)	UTS (Kg/mm ²)	%EL.	%RA	Impact Values (Joules)		Macrostructure As per ASTM-381	Matrix
						Izod	Charpy		
Spec.	240 Max.	-	-	-	-	-	-	Better Than C2R2S2	Uniform distribution of Ferrite plus Pearlite
Actual Value	206-217	-	-	-	-	-	-	C2R2S2	Uniform distribution of Ferrite plus Pearlite

Metallurgical Properties

Test Code	Decarb ASTM J419 (mm)	Grain Size as per ASTM E112	Inclusion Rating (As per IS 4163/ ASTM 454) Plate IR					Magnaflux Test (100% Bars)	UT Test (100% Bars)	Spark/ Spectral Test (100% Bars)
			Series	A	B	C	D			
Spec.	-	6.0 / 8.0	T / H	2.0 / 1.0	2.0 / 0.0	2.0 / 0.0	2.0 / 1.0	-	-	-
Actual Value	-	6.0 / 7.0	T / H	1.5 / 0.5	0.5 / 0.0	0.0 / 0.0	1.5 / 0.5	OK	OK	-

Hardenability Test Result

Jominy Distance (mm/finch)	J 7/16"									
Spec (HRC)	34-37									
Actual Hardness (HRC)	35.00									

Remarks : Material is conforming to the customer specification.

NOTE:- This material is made for AL, and is complying to AL Std 258.02

DECLARATION : TEST RESULTS ARE BASED ON ACTUAL TESTS CARRIED OUT ON SAMPLES DRAWN AS PER QUALITY ASSURANCE PLAN. TEST CERTIFICATE CONFORMS TO THE CUSTOMER TDC.



(AUTHORISED SIGNATORY)