



R. L. STEELS & ENERGY LTD.

TEST CERTIFICATE

Regd. Office: Gut No. 78 to 81, Pangra Shiver Chitegaon, Paithan Road, Aurangabad - 431 107
Maharashtra, India. Phone : 02431-661231, 251163 Fax : 02431-251879
E-mail : qc@rlsteels.com, Website : www.rlsteels.com

Format No. : FT/QAD/03
Issue Dt : 01/10/2017
Rev No. : 00

Customer: M/S HAPPY FORGINGS.LTD.(UNIT II)

B- XXIX-2254/1 & OPP. HINDUSTAN TYRES (ADJ. WARYAM STEELS), KANGANWAL ROAD, PO-JUGIANA, LUDHIANA.

General Information & Material Details

TC NO.	Date	Invoice No.	Date	Truck No.	No. of Pcs	Quantity in MT	Length	Supply Condition	Colour code
18-0777	30-05-2018	RL18-SI-0781	30-05-2018	RJ 07 GA 7781	154	25.770	5.0 to 6.0 MTR	AS ROLLED	YELLOW+ BLUE+WHITE
Process Route		Heat No.	Grade	As Cast Size		Product Size		Reduction Ratio	Customer TDC
EAF/LRF/VD/CCP-with MEMS		2-YDQ-4	EN353	180X220		63RCS		9.97:1	-

Chemical Composition & Tramp Elements

Element	%C	%Si	%Mn	%P	%S	%Cr	%Ni	%Mo	%Cu	%V	%Al	%Ti	%B	%Ca	%As
Min.	0.14	-	0.50	-	0.020	0.75	1.00	0.08	-	-	0.020	-	-	-	-
Max.	0.20	0.35	1.00	0.035	0.040	1.25	1.50	0.15	-	-	0.040	-	-	-	-
Actual	0.19	0.22	0.95	0.033	0.026	1.14	1.03	0.136	-	-	0.023	-	-	-	-

Tramp Elements (Contd.) & DI / CE

Element	%Sn	%Pb	%Sb	CE	DI Value	Gas Analysis.				Dimension Tolerance	
						Gas (PPM)	O2	H2	N2	Size Tol. (MM)	-
Min	-	-	-	-	-		-	-	-	Specification	As per IS 3739, Grade I.
Max	-	-	-	-	-		20.00	2.50	90.00		
Actual	-	-	-	-	-		14.00	1.10	75.00		

Mechanical Properties

								Macrostructure	Microstructure	
Test Code	Hardness As Rolled (BHN)	Hardness (H&T Condition) (BHN)	YS (Kg/mm²)	UTS (Kg/mm²)	%El.	%RA	Impact Values (Joules)		Macrostructure As per ASTM E-381	Matrix
							Izod	Charpy		
Spec.	240 Max.	-	-	-	-	-	-	-	Better Than C2R2S2	Uniform distribution of Ferrite plus Pearlite
Actual Value	206-217	-	-	-	-	-	-	-	C2R1S1	Uniform distribution of Ferrite plus Pearlite

Metallurgical Properties

								Other Test Results			
Test Code	Decarb ASTM J419 (mm)	Grain Size as per ASTM E112	Inclusion Rating (As per IS 4163/ ASTM E-45A) Plate IR					Magnaflux Test (100% Bars)	UT Test (100% Bars)	Spark/ Spectral Test (100% Bars)	
			Series	A	B	C	D				
Spec.	-	6.0 / 8.0	T / H	2.0 / 1.0	2.0 / 0.0	2.0 / 0.0	2.0 / 1.0	-	-	-	-
Actual Value	-	6.0 / 7.0	T / H	1.5 / 0.5	0.5 / 0.0	0.0 / 0.0	1.5 / 0.5	OK	OK	OK	-

Hardenability Test Result

Jominy Distance (mm/inch)	J 7/16"										
Spec (HRC)	37-41										
Actual Hardness (HRC)	38.00										

Remarks : Material is conforming to the customer specification.

NOTE:- This material is made for AL, and is complying to AL Std 258.02

DECLARATION : TEST RESULTS ARE BASED ON ACTUAL TESTS CARRIED OUT ON SAMPLES DRAWN AS PER QUALITY ASSURANCE PLAN. TEST CERTIFICATE CONFORMS TO THE CUSTOMER TDC.

For R L STEELS & ENERGY

(AUTHORISED SIGNATORY)

