

R. L. STEELS & ENERGY LTD.

TEST CERTIFICATE

Regd. Office: Gut No. 78 to 81, Pangra Shiver Chitegaon, Paithan Road, Aurangabad - 431 107 Maharashtra, India. Phone: 02431-661231, 251163 Fax: 02431-251879 E-mail: qc@risteels.com, Website: www.risteels.com Format No. : FT/QAD/01 Issue Dt :10/08/2014, Rev No.: 01

(AUTHORISED SIGNATORY

Custome	er: M/	S SADH	U FOR	SING L	TD.										
UNIT-2,PLO	T NO-8	4,SECTOR-	25, FARIDA	ABAD-121	001										
General Inf	ormati	on & Mate	erial Detai	ls				management would be a second party	100						
TC NO. Date		Invoice No.		Date	Truck No.		No. of PCS	Quantity In	Length	Suj	ply Condition		Color	ur code	
17-4641 06-03-2018		RL17-SI-4248		06-03-2018	RJ 19 GF 9088		9	3.040	5.0 TO 6.0 MTR	AS ROLLED			YELLOW+BLUE+		
Process Route		Heat No.		Grade		As Cast Size		Product Size		Reduction Ratio		C	Customer TDC		
EAF/LRF/VD/CCP-with MEMS			2-WLY-4		EN353		240X280		90RCS		8.29:1		As por TATA MOTORS SS-40		
Chemical C	ompo	sition & T	ramp Eler	nents											
Element	%C	%Si	%Mn	%P	%S	%Cr	%Mo	%Ni	%Cu	%V	%AI	%Ті	%В	%Ca	%As
Min.	0.14	-	0.50	-	0.020	0.75	0.080	1.00	-		0.020	-	-	-	-
Max.	0.20	0.35	1.00	0.035	0.040	1.25	0.15	1.50	-	-	0.040	-	-		-
Actual	0.190	0.25	1.00	0.030	0.026	1.13	0.135	1.02	-	-	0.026		-		
Tramp Elements (Contd.) & DI / CE							· G	Gas Analysis.			Dimension			nce	
Element	%Sn	%Pb	%Sb	CE	DI Value				02	H2	N2 Size Tol. (MM)		ol. (MM)	-	
Min	-						Gas (PPM)	Min	-	,-	70.00				
Max	-	-	-	-	-			Max	20.00	2.00	100.00	Specif	Specification As		As per IS 3739, Grade I.
Actual . (0.005	-	-		-			Actual	12.00	1.30	76.00				
Mechani <mark>ca</mark> l	Prope	rties									Macrost	ructure	Mic	rostruc	ture
Test Code As	Hardness As Rolled	Hardness (H&T Condition) (BHN)	YS (Mpa)		UTS (Mpa)		%EI.	%RA	Impact Values (Joules)		Macrostructure As				
(1	BHN)								Ized	Charpy					
Spec. 24	10 Max.	•	*						-	-	Better Tha	Better Than C2R2S2			
Actual Value	06-217		-		F		-				C2R2S2				
Vletallurgica	al Prop	erties									Other T	est Res	uits	allings a.	
Test Code		Decarb ASTM J419	Grain Size as per ASTM	Inclusion Rating (As per I		per IS 4163/	r IS 4163/ ASTME-45A)		Magnaflux Test (100%		UT Test	Spark/Sp ectral Test	-	Step Down Tes	
		(mm)	E112	Series	А	В	С	D	Ва	Bars)		(100% Bars)			
Spec.		-	5.0 / 8.0	T/H	2.0 / 1.0	2.0 / 0.0	2.0 / 0.0	2.0 / 0.0	-						
Actual Value		-	6.0 / 7.0	T/H	1.5 / 0.5	/ 0.5 0.5 / 0.0		1.5 / 0.0	ОК		ок	ок		ок	
lardenabilit	ty Test	Result					Account of the second s	h			4 -				
Jominy . Distance J (mm/inch)	J 1.5	J 5.0	J 10.0	J 30.0											
Spec (HRC)		-	38-42		the error handra, in change of an America, or i				Annual Vision to 11 annual to 1						
Actual		43.50	39.00	29.00		THE RESTRICTION OF THE PARTY OF	VT- 4 1-4 1-4-1				***************************************				
	5.00	43.50	33.00	20.00	1					1		1		waterest strings	

DECLARATION: TEST RESULTS ARE BASED ON ACTUAL TESTS CARRIED OUT ON SAMPLES DRAWN AS PER QUALITY ASSURANCE PLAN. TEST CERTIFICATE CONFORMS TO THE CUSTOMER TDC.