



Month: August 2025
Supersedes all earlier TDS

KTA 6000 GRANITEFIX - TYPE 4 | C2TES1

Description

KTA 6000 is a high polymer modified and highly flexible adhesive with enhanced slip resistant and bonding strength specially developed to fix large format granite slabs and stones. Suitable for internal and external thick and medium bed applications.

Specification

Technical parameters conforms with IS 15477, EN 12004

Area of Application

KTA 6000 is recommended for fixing large format granite slabs and stones on external floors and walls (up to height of 40 feet).

Features & Benefits

- Ready to use, just add water
- Needs no curing
- Highly polymer modified - enhanced bonding strength
- Highly deformable adhesive - sustains vibrations
- Water, thermal and shock resistant
- Enhanced slip resistant for vertical applications

Application Method




Surface Preparation

- The surface should be sound and clean, free from dust, grease, oil, loose material, paint etc.
- The substrate must be level, cured, undamaged, rigid and free from any debonding agents.
- All slabs must be plumb and true with in 6mm in 3m.




Mixing

- Place clean water into a mixing bowl and add **KTA 6000** powder to it, use 4.5 - 5 litres of water and mix thoroughly until a slump free mortar is achieved.
- Mix it with hand or a slow speed drill for a homogenous mix and let it slake for 5 minutes.
- Always mix required quantity which can be consumed within pot life.




Application

- Apply adhesive to the substrate with the flat side of the notch trowel and comb on additional adhesive with the notched side.
- Back butter large format stones (> 300 mm) to provide full bedding and firm support.
- Press the stone firmly into position with a slight twisting action and beat it using rubber mallet to imbed the stone and adjust level.



KTA 6000



Technical Data As Per Relevant IS and ASTM Standards

Water Powder Ratio	25 %
Bulk Density	1500 - 1600 kg / m3
Pot Life	Approx 100 minutes
Open Time	Approx 35 minutes
Adjustable Life	Approx 25 minutes
Time to Traffic	24 hours
Tensile Adhesion Strength as per EN 12004	≥ 1.5 N / mm2
Application Temperature	5°C to 35°C
Adhesive Thickness	3 mm - 12 mm
Coverage @ 6mm / kg	2 Sq. ft.
Tensile Adhesion at Dry Condition	2.85 N / mm2
Tensile Adhesion at Wet Condition	2.69 N / mm2
Compressive Strength	16.94 N / mm2
Shear Adhesion at Dry Condition	3.04 N / mm2
Shear Adhesion at Wet Condition	2.58 N / mm2
Shear Adhesion at Heat aging	2.70 N / mm2
Slip Resistance (T)	0.11 mm

Precautions

- Always add powder to water and never add excess water than recommended.
- Not suitable for tiling over flexible substrates, such as fibrous cement sheeting, plasterboard and timber.
- Control joints should be provided at every 3m height to accommodate contractions and expansions.
- Do not use adhesive to correct surface irregularities greater than 15 mm.
- Protect from direct rainfall / foot traffic for at least 24 hours.
- Never add sand and cement at site.

Coverage

- Approx 50 - 60 square feet / 20 kg bag at 3 mm thickness (using 6 mm x 6 mm notch).
- Approx 30 - 40 square feet / 20 kg bag at 6 mm thickness (using 6 mm x 6 mm notch).

*Coverage will vary depending on trowel notch size, type, size of tile and surface smoothness and evenness.

Sobhraj Developments Private Limited
Khasra No. 267, Near Kumawat Petrol Pump, Nasirabad Road, Mangliawas Ajmer 305023 INDIA
Tel: +91 94140 09900 Email: info@ktasolutions.in Web: www.ktasolutions.in

DISCLAIMER: While the company guarantees its products against defective material, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this data sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information please contact the company office in your location.

