

TECHNICAL BULLETIN

DIXIE CHEMICAL
10601 Bay Area Blvd.
Pasadena, TX 77507
Tel: (281) 474-3271
Fax: (281) 291-3384
E-Mail: info@dixiechemical.com

DCE 142
(Diglycidyl 1,2-cyclohexanedicarboxylate)
CAS Registry Number 5493-45-8

Typical Properties

Property	Typical Values	Test Method
Appearance	Clear to Light Yellow Liquid	D-104 (Visual)
Viscosity at 25°C, cPs	500 – 1,300	D-150F
Epoxy Equivalent Weight, g/mol	160 - 181	D-144
Specific Gravity, 25°C	1.20 – 1.25	D-102
Residual ECH, ppm	0 - 50	D-657D
Color, Gardner	0 - 3	D-150G
Flash Point	> 336°F (169°C)	ASTM D-93
Refractive Index, 25°C	1.480 – 1.491	D-107

Applications

Diglycidyl 1,2-cyclohexanedicarboxylate or DCE 142 is a low viscosity cycloaliphatic diepoxy. The cured resins of DCE 142 with carboxylic anhydrides will have excellent mechanical properties, high Tg, high weather/chemical resistance, and superior electrical resistance along with non-yellowing characteristics. DEC 142 is ideal for applications such as coatings, electrical insulation components designed for medium/high voltage, outdoor applications, and high performance/temperature composites.

TECHNICAL BULLETIN

DCE 142

Health Hazards

Read and understand the Safety Data Sheets (SDS) before use. DCE 142 primarily causes skin and eye irritations.

Handling

Follow the recommendations in the SDS for personal protective equipment when handling the material. At a minimum, it requires protective chemical goggles, impenetrable gloves, and measures to avoid breathing chemical vapors.

Use only with adequate ventilation. Avoid contact with skin, eyes, and clothing. In case of contact, follow the procedures outlined in the SDS. Generally, these procedures include immediately getting medical attention and flushing the affected skin or eyes with copious amounts of water for at least 15 minutes. Wash contaminated clothing before reuse.

Storage

This material is not compatible with strong acids/bases or strong oxidizing agents. Store in a dry, cool, and well-ventilated area. Keep away from direct sunlight, heat, hot surfaces, sparks, open flames, and other ignition sources.

Availability

DCE 142 is available from Dixie Chemical in Pasadena, TX. Contact your Dixie representative for details.