

TECHNICAL BULLETIN


DIXIE CHEMICAL
10601 Bay Area Blvd.
Pasadena, TX 77507
Tel: (281) 474-3271
Fax: (281) 291-3384
E-Mail: info@dixiechemical.com

Hexadecenylsuccinic Anhydride (ASA 100)

Typical Properties


Property	Values	Test Method
Physical Appearance	Clear Amber Liquid	D-104 (Visual)
Specific gravity @ 25 °C, g/cc	0.945-0.965	D-102 (ASTM D 4052)
Gardner Color	10 Max	D-150G
Viscosity at 25°C, cP	90-175	D-150F
Residual Olefin, %	1 Max	D-150M
HDSA, %	95 Min	D-150M
Free Acid, %	1.5 Max	D-150M
Neut. Number, mg KOH/g	330-355	D-150I
Pour Point °C	-34	ASTM D97
Freeze Point °C	-21	ASTM D1015

Viscosity as a Function of Temperature



The data contained herein are furnished for information only and are believed to be reliable. This information is provided only as guidance and is not to be considered a warranty or quality specification. Dixie Chemical Company, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

TECHNICAL BULLETIN ASA 100



Applications

Hexadecenylsuccinic Anhydride (ASA 100) is an alkenylsuccinic anhydride (ASA) based on C16 alpha-olefin. ASAs such as ASA 100 are commonly used as alkaline paper sizing agents. These products are easy to handle and can be employed in both cationic starch and polymer emulsion systems. ASAs are also used in a variety of other products. In metal working fluids, ASAs are utilized as corrosion inhibitors. ASAs are often used in fuel and lubricant additives including pour point depressants, corrosion inhibitors and dispersants. ASAs find use as intermediates for surfactants and can also be converted to acid amides and esters. Other suggested applications are in plasticizers, epoxies, and moisture control for leather goods.

Dixie's ASA 100 is available with or without surfactant. Two types of surfactant are available, dioctylsulfo-succinate (DOSS) or phosphate ester.

TECHNICAL BULLETIN

ASA 100

Registration

ASA 100 is REACH registered as a component under the name 2,5-Furandione,dihydro-,mono-C15-20-alkenyl derivs. The CASRN is 68784-12-3 and the REACH registry number is 01-2119533117-46. In the US, CASRN 32072-96-1 is typically used for HDSA.

Handling & Storage

ASA 100 must be stored out of contact with moisture to avoid hydrolysis of the anhydride to the acid. When properly stored, ASA 100 has a shelf life of 24 months.

ASA storage tanks may be constructed of mild steel, 304 or 316 stainless steel. If protection from atmospheric moisture is difficult then 304 or 316 are preferred due to the formation of corrosive acids by the interaction of ASA with water. For more information on the design of bulk storage for ASA products, consult the Dixie Chemical brochure "Alkenylsuccinic Anhydride Storage Requirements."

Health Hazards

Read and understand the relevant Safety Data Sheets (SDS) for all products before use. ASA 100 is a mild primary skin irritant. Avoid contact with skin, eyes and clothing. Use only with adequate ventilation. In case of contact, immediately flush skin or eyes with plenty of water for at least 15 minutes; for eyes, get medical attention. Wash contaminated clothing before reuse.

Availability

ASA 100 is available from Dixie Chemical in Pasadena, TX. Contact your Dixie representative for details.