

TECHNICAL BULLETIN

DIXIE CHEMICAL

10601 Bay Area Blvd.
Pasadena, TX 77507
Tel: (281) 474-3271
Fax: (281) 291-3384
E-Mail: info@dixiechemical.com

DCE 8 CASRN 68609-97-2

Typical Properties

Properties	Value	Test Method
Molecular Weight (g/eq)	285 - 310	D-144
Appearance	Clear Liquid	D-104 (Visual)
Viscosity @ 25 °C, cP	5 - 10	D-237
APHA Color	50 max.	D-103
Epichlorohydrin, ppm	10 max.	D-144A
Water, %	0.1 max.	D-101
Hydrolyzable Chloride, %	0.1 max.	D-657A

Applications

DCE 8 is a low viscosity reactive diluent. It is an alkyl (C12-14) glycidyl ether.

DCE 8 has the following characteristics:

- Exceptional viscosity reducer for epoxy resins
- Low odor
- Low color
- Aids in fiber wet out in composite applications

This reactive diluent is designed to be used in conjunction with liquid epoxy resins for a wide variety of composite and coating applications.

Modifying the Viscosity of Epoxy Resins

The data contained herein are furnished for information only and are believed to be reliable. This information is provided only as guidance and is not to be considered a warranty or quality specification. Dixie Chemical makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

TECHNICAL BULLETIN

DCE 8

DCE 8 is useful in modifying the viscosity of epoxy resins. The following Table shows how DCE 8 lowers the viscosity of a BPA standard epoxy resin.

	Sample A	Sample B	Sample C	Sample D
DCE 8 (wt. %)	0%	10%	15%	20 %
Viscosity (cps)	13,917	1,917	940	540

Handling & Storage

DCE 8 should be stored between 4° C (39° F) and 40° C (104° F) in a cool, dry, well-ventilated place. For best results, keep the container tightly closed and avoid extreme temperatures.

Safety

Read and understand the relevant Safety Data Sheets (SDS) for all products before use. DCE 8 is a skin irritant and may cause an allergic skin reaction. Avoid contact with skin, eyes and clothing. Use only with adequate ventilation. In case of contact, follow the procedures outlined in the SDS.

Follow the recommendations in the SDS for personal protective equipment when handling this material.

Availability

DCE 8 is available from Dixie Chemical in Pasadena, Texas. Contact your Dixie representative for details.