

TECHNICAL BULLETIN

DIXIE CHEMICAL

10601 Bay Area Blvd.

Pasadena, TX 77507

Tel: (281) 474-3271

Fax: (281) 291-3384

E-Mail:


info@dixiechemical.com

HHPA 7030 NC

Typical Properties


Property	Values	Test Method
Molecular Weight	158	
Appearance	Clear and free of Particulate matter	D-104
APHA Color	50 Max	D-103 (ASTM D 1209)
HHPA, %	68-72	D-160
Total Anhydride, %	99 Min	D-160
Acid, %	1 Max	D-160N
Brookfield Viscosity, cPs	70-115	D-150F

Viscosity as a Function of Temperature



The data contained herein are furnished for information only and are believed to be reliable. This information is provided only as guidance and is not to be considered a warranty or quality specification. Dixie Chemical Company, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

TECHNICAL BULLETIN
HPHA 7030 NC



About

HPHA 7030 NC is a low viscosity, clear liquid designed for curing epoxy resins and for other polymer applications. It is a blend of 70 parts hexahydrophthalic anhydride and 30 parts methylhexahydrophthalic anhydride.

Applications

The low viscosity of HPHA 7030 NC and its high mix ratio with epoxy make the product particularly suitable for use in composite applications with high fiber loadings. It is commonly used to cure epoxy resins in potting, encapsulation, filament windings, and clear castings.

For more information on the use of anhydrides like HPHA 7030 NC as epoxy curing agents, please consult the Technical Bulletin, FORMULATING ANHYDRIDE-CURED EPOXY SYSTEMS, available from Dixie Chemical Company.

TECHNICAL BULLETIN

HPHA 7030 NC

Handling & Storage

HPHA 7030 NC will react with water to form diacids. This is normally undesirable, so HHPA 7030 NC should be stored in such a way that it is carefully protected from moisture contamination. When properly stored, HHPA 7030 NC has a shelf life of 24 months.

Health Hazards

Read and understand the relevant Safety Data Sheets (SDS) for all products before use. These anhydrides are primary skin and eye irritants. Avoid contact with skin, eyes, and clothing. Use only with adequate ventilation. In case of contact, follow the procedures outlined in the SDS. Generally, these procedures include immediately flushing the affected skin or eyes with copious amounts of water for at least 15 minutes. In the case of eye contact, get medical attention. Wash contaminated clothing before reuse.

Follow the recommendations in the SDS for personal protective equipment when handling these materials. At a minimum, these procedures typically include protective chemical goggles, impenetrable gloves, and measures to avoid breathing chemical vapors.

Availability

HPHA 7030 NC is available from Dixie Chemical in Pasadena, Texas. Contact your Dixie representative for details.