



Report No: URPT-20260918-0015

Date: 18-09-2026

TEST CERTIFICATE / REPORT

California Bearing Ratio

Retest — Execution #17 (Previous: #10138)

Report No.: URPT-20260918-0015

Report Status: RELEASED

Issue Date: 18-09-2026

Report Revision: 12

ULR No.: -

Result Revision: 2

1. Report & Test Identity

Test Execution ID	10145	Test Group	10042
Test Name	California Bearing Ratio	Test Category	SOIL_CBR
Discipline	-	Department	Geotechnical / Soil Department
Test Location	Devine Laboratory	Execution / Run No.	17
Retest	YES	Previous Execution	10138

2. Sample Information

Sample ID	TX-B5-SOIL-001	Registration No.	DMSPL-B5-001
Sample Type	SUBGRADE	Description	Subgrade Soil Sample KM 42+500
Quantity	-	Unit	-
Received Date	16-09-2026	Test Start Date	17-09-2026
Completion Date	17-09-2026		
Sampling Information			
Sampling Date	-	Sampled By	-
Sampling Method	-	Sampling Location	-

3. Customer / Request Information

Customer Name	Dhruv	Contact Person	-
Customer Address	South Bopal, Ahmedabad, 380058	Contact Details	-
Customer Request No.	DMSPL-B5-001	Customer Reference	-
Project / Work Order	-		

4. Test Method & Specification

Test Method	California Bearing Ratio	Method Code	IS 2720 (Part 16)
Method Version	1987	Method Effective Date	-
Specification	PROJECT_SUBGRADE_CBR_SPEC - Project Subgrade CBR Specification	Specification Version	-
Product / Material	-	Grade	SUBGRADE
Classification	-		

Applicable Requirement: PROJECT_SUBGRADE_CBR_SPEC - Project Subgrade CBR Specification
Decision Rule: ALL_REQUIRED_PASS

5. Test Conditions

Only configured / applicable conditions are displayed.

Condition	Value	Unit / Description
- — Curing Age	= -	-
- — Moisture Condition	= -	-
- — Specimen Thickness	= -	mm

6. Equipment & Metrological Traceability

Only equipment used / relevant to the frozen execution is displayed.

Equipment	ID / Serial No.	Traceability / Calibration
Casagrande Apparatus	EQ-SOIL-CAS-01	- (valid upto -)

7. Test Results & Conformity

No.	Test Parameter	Unit	Result	Requirement	Verdict
1	MOISTURE_CONTENT — Moisture Content	%	12.50	8.000000 - 12.000000	FAIL
2	DRY_DENSITY — Dry Density	g/cc	1.80	1.700000 - 2.000000	PASS
3	MAX_DRY_DENSITY — Maximum Dry Density	g/cc	2.00	1.600000 - 2.400000	PASS
4	COMPACTION — Compaction	%	90.00	95.000000 - 100.000000	FAIL



Report No: URPT-20260918-0015

Date: 18-09-2026

No.	Test Parameter	Unit	Result	Requirement	Verdict
5	SAMPLE_PREPARATION_MOISTURE – Preparation Moisture	%	11.00	8.000000 - 14.000000	PASS
6	SURCHARGE_LOAD – Surcharge Load	kg	5.00	4.000000 - 6.000000	PASS
7	PENETRATION_2_5MM_LOAD – Load at 2.5 mm Penetration	kN	6.60	0.500000 - 2.000000	FAIL
8	PENETRATION_5_0MM_LOAD – Load at 5.0 mm Penetration	kN	9.90	0.800000 - 2.500000	FAIL
9	CBR_2_5 – CBR at 2.5 mm	%	50.00	5.000000 - 15.000000	FAIL
10	CBR_5_0 – CBR at 5.0 mm	%	50.00	5.000000 - 15.000000	FAIL
11	CBR_RESULT – CBR Result	%	50.00	6.000000 - 100.000000	PASS

Result Interpretation: PASS / FAIL / INFORMATIONAL / NOT APPLICABLE

Overall Decision: **FAIL**

Decision Basis: ALL_REQUIRED_PASS

8. Calculation / Derived Results

Parameter	Unit	Final Result	Calculation / Source
COMPACTION – Compaction	%	90.00	$\frac{(\text{DRY_DENSITY})}{(\text{MAX_DRY_DENSITY})} \times 100$ $[(1.80/2.00) \times 100 = 90.00]$
CBR_2_5 – CBR at 2.5 mm	%	50.00	$\frac{(\text{PENETRATION_2_5MM_LOAD})}{(13.2)} \times 100$ $[(6.60/13.2) \times 100 = 50.00]$
CBR_5_0 – CBR at 5.0 mm	%	50.00	$\frac{(\text{PENETRATION_5_0MM_LOAD})}{(19.8)} \times 100$ $[(9.90/19.8) \times 100 = 50.00]$
CBR_RESULT – CBR Result	%	50.00	$\text{MAX}(\{\text{CBR_2_5}\}, \{\text{CBR_5_0}\})$ $[\text{MAX}(50.00, 50.00) = 50.00]$

Calculation values shown here are read from the finalized result lineage. No calculation is performed by the report renderer.

9. Measurement Uncertainty

U = 2.500000 % | Coverage probability / confidence: - | Coverage factor (k): 2.0000 | Basis: Type B

Parameter	Result	U	Coverage Factor (k)
MOISTURE_CONTENT – Moisture Content	12.50	-	-
DRY_DENSITY – Dry Density	1.80	-	-
MAX_DRY_DENSITY – Maximum Dry Density	2.00	-	-
COMPACTION – Compaction	90.00	-	-
SAMPLE_PREPARATION_MOISTURE – Preparation Moisture	11.00	-	-
SURCHARGE_LOAD – Surcharge Load	5.00	-	-
PENETRATION_2_5MM_LOAD – Load at 2.5 mm Penetration	6.60	-	-
PENETRATION_5_0MM_LOAD – Load at 5.0 mm Penetration	9.90	-	-
CBR_2_5 – CBR at 2.5 mm	50.00	-	-
CBR_5_0 – CBR at 5.0 mm	50.00	-	-
CBR_RESULT – CBR Result	50.00	-	-

U = expanded / configured uncertainty. If uncertainty is not configured for a parameter: U = -.

10. Compliance / Acceptance Summary

Parameter	Compliance Value	Effective Requirement	Margin / Delta	Verdict
MOISTURE_CONTENT – Moisture Content	12.500000	8.000000 - 12.000000	-	FAIL
DRY_DENSITY – Dry Density	1.800000	1.700000 - 2.000000	-	PASS
MAX_DRY_DENSITY – Maximum Dry Density	2.000000	1.600000 - 2.400000	-	PASS
COMPACTION – Compaction	90.000000	95.000000 - 100.000000	-	FAIL
SAMPLE_PREPARATION_MOISTURE – Preparation Moisture	11.000000	8.000000 - 14.000000	-	PASS
SURCHARGE_LOAD – Surcharge Load	5.000000	4.000000 - 6.000000	-	PASS
PENETRATION_2_5MM_LOAD – Load at 2.5 mm Penetration	6.600000	0.500000 - 2.000000	-	FAIL
PENETRATION_5_0MM_LOAD – Load at 5.0 mm Penetration	9.900000	0.800000 - 2.500000	-	FAIL
CBR_2_5 – CBR at 2.5 mm	50.000000	5.000000 - 15.000000	-	FAIL
CBR_5_0 – CBR at 5.0 mm	50.000000	5.000000 - 15.000000	-	FAIL
CBR_RESULT – CBR Result	50.000000	6.000000 - 100.000000	-	PASS

Total Evaluated

11 Parameters

Conforming (PASS)

5 Parameters



Report No: URPT-20260918-0015

Date: 18-09-2026

Non-Conforming (FAIL)	6 Parameters	Statement of Conformity	FAIL
Applied Decision Rule	ALL_REQUIRED_PASS	Tolerance Applied	None
Tolerance Source	-	Guard Banding / MU	Direct Evaluation

11. Accreditation & Scope Information

Accreditation Status	Active	Certificate No.	TC5098
Accreditation Location	Devine Laboratory	Scope Status	WithinScope
NABL Symbol Status	APPLICABLE	ULR Status	NOT APPLICABLE
ULR No.	-		

Scope Statement: 3
ULR Note: Soil & Rock testing exempt under NABL ULR policy (Clarification 15.06.2026)
Accreditation claims are limited to the applicable accredited scope. Non-accredited results shall not be represented as accredited results.

12. Review, Verification & Approval

Stage	Performed By	Date / Time	Status
Tested By	System Admin	17 Sep 2026 17:10	Completed
Reviewed By	System Admin	-	Reviewed
Verified By	Super Admin	17 Sep 2026 19:25	Verified
Approved By	Sudhanshu Singh	17 Sep 2026 19:25	Approved

Approval Status: APPROVED

Review Remarks: R8-05 verified
Approval Remarks: R8-08 approved
Findings: 2 total, 1 open

13. Report Authentication

Report No.: URPT-20260918-0015 | Report Revision: 12 | ULR No.: -
Verify this report online using the verification QR code or authentic URL reference.
Document Hash / Integrity Reference: 1b576280ed7098ff43cdacd500b1e5c2f52b6f8c1ad71b1fbb447914500ed7ec

14. Declarations, Terms & Conditions

- Results relate only to the sample / test item identified in this report as received by the laboratory.
- This test report shall not be reproduced except in full without written approval of the testing laboratory.
- Metrological traceability of test results and measurement standards is maintained through valid calibration.
- Accreditation claims and NABL Symbol apply only to the tests and parameters covered under valid scope.
- Any amendments, corrections, or reissues are tracked under distinct Report Revision numbers and audit trail.

System Admin

Super Admin

Sudhanshu Singh



Verify Online