



TEST CERTIFICATE / REPORT
Tensile Test at Ambient Temperature

Report No.: URPT-20260925-0001
Report Status: GENERATED
Issue Date: 25-09-2026

Report Revision: 1
ULR No.: -
Result Revision: 1

1. Report & Test Identity

Test Execution ID	1	Test Group	1
Test Name	Tensile Test at Ambient Temperature	Test Category	TENSILE_TEST
Discipline	-	Department	Mechanical Testing Laboratory
Test Location	Devine Laboratory (Head Office)	Execution / Run No.	1
Retest	NO	Previous Execution	-

2. Sample Information

Sample ID	26-000001	Registration No.	DMSPL-000001
Sample Type	Fe 500D	Description	TMT Rebar 16mm Fe 500D Heat H-101
Quantity	-	Unit	-
Received Date	25-09-2026	Test Start Date	25-09-2026
Completion Date	25-09-2026		
Sampling Information			
Sampling Date	-	Sampled By	-
Sampling Method	-	Sampling Location	-

3. Customer / Request Information

Customer Name	E2E STEEL WORKS	Contact Person	-
Customer Address	14 GOPAL INDUSTRIAL ESTATE ODHAV AHMEDABAD, 382415	Contact Details	-
Customer Request No.	DMSPL-000001	Customer Reference	-
Project / Work Order	-		

4. Test Method & Specification

Test Method	Tension Testing of Metallic Materials	Method Code	IS 1608 (Part 1):2022
Method Version	Part 1:2022	Method Effective Date	-
Specification	IS_1786 - High Strength Deformed Steel Bars for Concrete Reinforcement	Specification Version	-
Product / Material	-	Grade	Fe 500D
Classification	-		

Applicable Requirement: IS_1786 - High Strength Deformed Steel Bars for Concrete Reinforcement
Decision Rule: ALL_REQUIRED_PASS

5. Test Conditions

No conditions configured –

6. Equipment & Metrological Traceability

Only equipment used / relevant to the frozen execution is displayed.

Equipment	ID / Serial No.	Traceability / Calibration
UTM-101	UTM-101-1000KN / UTM_TENSILE_1000KN	- (valid upto -)

7. Test Results & Conformity

No.	Test Parameter	Unit	Result	Requirement	Verdict
1	YIELD_STRENGTH – Yield Strength	MPa	525.50	500.000000 - -	PASS
2	TENSILE_STRENGTH – Tensile Strength	MPa	580.00	545.000000 - -	PASS
3	ELONGATION – Elongation	%	18.50	16.000000 - -	PASS

Result Interpretation: PASS / FAIL / INFORMATIONAL / NOT APPLICABLE

Overall Decision: PASS

Decision Basis: ALL_REQUIRED_PASS

8. Calculation / Derived Results

No calculated / derived results.

9. Measurement Uncertainty

U = 3.000000 % | Coverage probability / confidence: - | Coverage factor (k): 2.0000 | Basis: Type B



Date: 25-09-2026

Parameter	Result	U	Coverage Factor (k)
YIELD_STRENGTH – Yield Strength	525.50	-	-
TENSILE_STRENGTH – Tensile Strength	580.00	-	-
ELONGATION – Elongation	18.50	-	-

U = expanded / configured uncertainty. If uncertainty is not configured for a parameter: U = -.

Parameter	Compliance Value	Effective Requirement	Margin / Delta	Verdict
YIELD_STRENGTH – Yield Strength	525.500000	500.000000 - -	-	PASS
TENSILE_STRENGTH – Tensile Strength	580.000000	545.000000 - -	-	PASS
ELONGATION – Elongation	18.500000	16.000000 - -	-	PASS

Total Evaluated	3 Parameters	Conforming (PASS)	3 Parameters
Non-Conforming (FAIL)	0 Parameters	Statement of Conformity	PASS
Applied Decision Rule	ALL_REQUIRED_PASS	Tolerance Applied	None
Tolerance Source	NONE	Guard Banding / MU	Direct Evaluation

Accreditation Status	NotAccredited	Certificate No.	-
Accreditation Location	Devine Laboratory (Head Office)	Scope Status	NoEffectiveScope
NABL Symbol Status	NOT APPLICABLE	ULR Status	NOT APPLICABLE
ULR No.	-		

Scope Statement: -

ULR Note: Laboratory is not accredited

This test is not covered under NABL accreditation; reported as a non-accredited laboratory result.

Stage	Performed By	Date / Time	Status
Tested By	-	25 Sep 2026 14:52	Completed
Reviewed By	-	-	Reviewed
Verified By	System Admin	25 Sep 2026 14:54	Verified
Approved By	Super Admin	25 Sep 2026 14:56	Approved

Approval Status: APPROVED

Report No.: URPT-20260925-0001 | Report Revision: 1 | ULR No.: -

Report No.: SRM/2023/23-0001 | Report Revision: 1 |
Verify this report online using the verification QR code or authentic URL reference.

Document Hash / Integrity Reference: 102127721ad7393f5f549a9cb54c6dc2e168256f47cba4cf26e5e193f9b2fd3c

1. Results relate only to the sample / test item identified in this report as received by the laboratory.
2. This test report shall not be reproduced except in full without written approval of the testing laboratory.
3. Metrological traceability of test results and measurement standards is maintained through valid calibration.
4. Accreditation claims and NABL Symbol apply only to the tests and parameters covered under valid scope.
5. Any amendments, corrections, or reissues are tracked under distinct Report Revision numbers and audit trail.

—

System Admin

Super Admin



Verify Online