

TEST REPORT

Applicant : FUZHOU HC HOME CO., LTD
Address : RM 203, Building 47, Gongjiao Courtyard, No.1 Sheng Fu Road, Gulou District,
Fuzhou, Fujian, China
Manufacturer : FUZHOU HC HOME CO., LTD
Address : RM 203, Building 47, Gongjiao Courtyard, No.1 Sheng Fu Road, Gulou District,
Fuzhou, Fujian, China

The following samples were submitted and identified on behalf of the clients as:

Sample Name : Wooden Kids Playhouse
Sample Description : No data available
Trade marks : No data available
Model No. : W2644P368997
Series number : No data available
Customer Statements : No data available
ASIN : No data available
Batch No. : 250812
Labeled Age Grading : 3-8 years old
Requested age grading : 3-8 years old
Age group applied in testing : 3-8 years old
Sample Received Date : Aug.11,2025
Testing Period : Aug.11,2025 to Aug.14,2025
Test Requested : Selected test (s) in the selected parts as requested by client.
Test Method : Please refer to next page(s).
Test Result : Please refer to next page(s).
CPSC Lab ID : 1885

Revised Statement NA

Laboratory Accreditation : IAS Testing Laboratory TL-1329

Signed for and on behalf of HRL

Dylan Chow
Dept Manager



**Dongguan Huanren Lab
Technology Co., Ltd**

All test reports issued by this laboratory are electronically signed using UKEY digital signatures. Reports with missing or damaged e-signatures shall be deemed invalid..

NOTE: IAS is International Accreditation Service. www.iasonline.org

IAS is ILAC/IAF Mutual Recognition Arrangement (MRA) Signatory.

Room 301, Building 2, No. 53 Jinyuan Road, Liaobu Town, Dongguan City, Guangdong Province, China

Tel: (86-769)13423451083 E-mail:CS@Labsoon.com <http://www.Labsoon.com>

TEST REPORT

Test Requested		Conclusion
A	As specified in title 16, code of federal regulations, chapter II - consumer products safety commission of U.S.A	--
	1. 16 CFR 1500.48 Sharp point	Pass
	2. 16 CFR 1500.49 Sharp edge	Pass
	3. 16 CFR 1500.50.51.52.53 Simulating use and abuse of toys	Pass
	4. 16 CFR 1501 Small Objects	NA
	5. 16 CFR 1500.44 Flammability of Solids	Pass
	6. 16 CFR 1610 Flammability Test of Clothing Textiles	NA
	7. 16 CFR 1303, Total Lead in Paints and Surface Coatings	Pass
	8. 16 CFR 1307 Determination of Phthalates	Pass
B	ASTM F963-23: Standard Consumer Safety Specification for toy Safety	Pass
	1.Mechanical and physical properties	Pass
	2. Flammability	Pass
	3. Total Lead in Substrate Materials Section 4.3.5.2(2)(a)	Pass
	4. Total Lead in Paints and Surface Coatings Section 4.3.5.1(1)	Pass
	5. Migration of certain elements in Substrate Materials Section 4.3.5.2	Pass
	6. Migration of certain elements in Paints and Surface Coatings Section 4.3.5.1(2)	Pass
	7. Phthalates Content Section 4.3.8	Pass
C	Consumer Product Safety Improvement Act of 2008 (CPSIA)	Pass
	1. CPSIA Sec.101.(a) Total Lead in Substrate Materials	Pass
	2. CPSIA Sec.101.(f) Total Lead in Paints and Surface Coatings	Pass
	3. CPSIA Sec.108 Determination of Phthalates	Pass
	4.CPSIA Sec.103 Tracking Labels for Children's Products /15 U.S. Code § 2063(a)(5)	Pass

TEST REPORT

Test Results:

Clause		Description	Result
1	16 CFR 1500.48	Technical requirements for determining a sharp point in toys and other articles intended for use by children under 8 years of age.	Pass
2	16 CFR 1500.49	Technical requirements for determining a sharp metal or glass edge in toys and other articles intended for use by children under 8 years of age.	Pass
3	16 CFR 1500.50.51.52.53	Normal use testing	Pass
		Abuse testing	Pass
		Impact test (53b)	Pass
		Bite test	N/A
		Flexure test	N/A
		Torque test(53e)	Pass
		Tension test(53f)	Pass
		Compression test(53g)	Pass
4	16 CFR 1501	Identifying toys and other articles intended for use by children under 3 years of age which present choking, aspiration, or ingestion hazards because of small parts.	N/A

A.5 16 CFR 1500.44 Method for determining extremely flammable and flammable solids

Sample	Burn rate (in/sec.)	NOTICE
Wooden Kids Playhouse	IBE	/

Remark:

1. DNI = Did not ignite (no time).
2. NA = Not Applicable
3. IBE = Ignited but self-extinguished before burn-rate could be determined (no time).
4. All styles of the submitted samples (and its accessories) was/were tested, the above result only showed the most severe burn rate of the samples.

TEST REPORT

A.6 16 CFR 1610 Flammability Test of Clothing Textiles

The 16 CFR 1610 standard categorizes the combustion performance of textiles into three levels: Level 1 for general flammability, Level 2 for moderate flammability, and Level 3 for rapid and intense combustion.

SAMPLE	Level requirements	Grade of level
Wooden Kids Playhouse	The combustion performance requirements for Level 1 textiles are: the average combustion time of fabric with no fuzz on the surface is greater than or equal to 3.5 seconds, the average combustion time of fuzz fabric is greater than or equal to 7 seconds, and the base fabric has no sparks or melting. The combustion performance requirement for Level 2 textiles is that the average combustion time of the fuzzy fabric is 4 seconds to 7 seconds. The combustion performance requirements for Level 3 textiles are: the average combustion time of fabric with no fuzz on the surface is less than 3.5 seconds, and the average combustion time of fabric with fuzz is less than 4 seconds.	N/A

A.7 16 CFR 1303, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E-1003-09.1 ,analyzed by Inductively Coupled Plasma-Optical Emission Spectrometry(ICP-OES).

Item	Unit	MDL	Results										Limit
			1	2	3	--	--	--	--	--	--	--	
Lead Content (Pb)	mg/kg	10	ND	ND	ND								90
Conclusion	/	/	Pass										/

Remark:N/A = Not Applicable

ND = Not Detected, less than the MDL



**Dongguan Huanren Lab
Technology Co., Ltd**

All test reports issued by this laboratory are electronically signed using UKEY digital signatures. Reports with missing or damaged e-signatures shall be deemed invalid..

NOTE: IAS is International Accreditation Service. www.iasonline.org

IAS is ILAC/IAF Mutual Recognition Arrangement (MRA) Signatory.

Room 301, Building 2, No. 53 Jinyuan Road, Liaobu Town, Dongguan City, Guangdong Province ,China

Tel: (86-769)13423451083

E-mail:CS@Labsoon.com

<http://www.Labsoon.com>

TEST REPORT

A.8 16 CFR 1307 Determination of Phthalates

Test Method: CPSC-CH-C1001-09.4, analyzed by Gas Chromatography with Mass Spectrometry(GC-MS).

Item	CAS No.	Unit	MDL	Results		Limit
				1+2+3	4+5+6	
Dibutyl phthalate (DBP)	84-74-2	mg/kg	50	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	mg/kg	50	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	mg/kg	50	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	mg/kg	50	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	mg/kg	50	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	50	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	50	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	mg/kg	50	ND	ND	1000
Conclusion	/	/	/	Pass		/

Item	CAS No.	Unit	MDL	Results		Limit
				7	--	
Dibutyl phthalate (DBP)	84-74-2	mg/kg	50	ND		1000
Benzyl butyl phthalate (BBP)	85-68-7	mg/kg	50	ND		1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	mg/kg	50	ND		1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	mg/kg	50	ND		1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	mg/kg	50	ND		1000
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	50	ND		1000
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	50	ND		1000
Di-n-pentyl phthalate (DPENP)	131-18-0	mg/kg	50	ND		1000
Conclusion	/	/	/	Pass		/

Remark:

(1)ND = Not Detected, less than the MDL

(2)MDL= Method Detected Limit

(3)mg/kg = ppm = parts per million



**Dongguan Huanren Lab
Technology Co., Ltd**

All test reports issued by this laboratory are electronically signed using UKEY digital signatures. Reports with missing or damaged e-signatures shall be deemed invalid..

NOTE: IAS is International Accreditation Service. www.iasonline.org

IAS is ILAC/IAF Mutual Recognition Arrangement (MRA) Signatory.

Room 301, Building 2, No. 53 Jinyuan Road, Liaobu Town, Dongguan City, Guangdong Province, China

Tel: (86-769)13423451083

E-mail:CS@Labsoon.com

<http://www.Labsoon.com>

TEST REPORT

B.1 ASTM F963-23: Standard Consumer Safety Specification for toy Safety - Mechanical and physical properties

Clause	Description	Result
4	Safety Requirements	
4.1	Material Quality **	Pass
4.3	Toxicology	Pass
4.3.5	Heavy Elements	Pass (see result)
4.3.5.1	Paint and Similar Surface-Coating Materials	Pass (see result)
4.3.5.2	Toy Substrate Materials	Pass (see result)
4.3.6	Cosmetics,Liquids,Pastes, Putties, Gels, Powders, and Items of Avian Feather Origin	NA
4.3.7	Stuffing Materials	NA
4.4	Electrical/Thermal Energy	NA
4.5	Sound-Producing Toys	NA
4.6	Small objects	Pass
4.6.2	Mouth-actuated Toys	NA
4.7	Accessible Edges	Pass
4.8	Projections	NA
4.9	Accessible Points	Pass
4.10	Wires or Rods	NA
4.11	Nails and Fasteners	NA
4.12	Plastic Film	NA
4.13	Folding mechanisms and hinges	NA
4.14	Cords, Straps and Elastic	NA
4.15	Stability and Over-Load Requirements	NA
4.16	Confined Spaces	NA
4.17	Wheels, Tires, and Axles	NA
4.18	Holes, Clearance & Accessibility of Mechanisms	NA
4.19	Simulated Protective Devices	NA
4.20	Pacifiers	NA
4.21	Projectile Toys	NA
4.22	Teethers and Teething Toys	NA
4.23	Rattles	NA
4.24	Squeeze Toys	NA
4.25	Battery-Operated Toys	NA
4.26	Toys Intended to be Attached to a Crib or Playpen	NA
4.27	Stuffed and Beanbag-Type Toys	NA
4.28	Stroller and Carriage Toys	NA



All test reports issued by this laboratory are electronically signed using UKEY digital signatures. Reports with missing or damaged e-signatures shall be deemed invalid..

NOTE: IAS is International Accreditation Service. www.iasonline.org

IAS is ILAC/IAF Mutual Recognition Arrangement (MRA) Signatory.

Room 301, Building 2, No. 53 Jinyuan Road, Liaobu Town, Dongguan City, Guangdong Province ,China

Tel: (86-769)13423451083

E-mail:CS@Labsoon.com

<http://www.Labsoon.com>

TEST REPORT

Clause	Description	Result
4.29	Art Materials	NA
4.30	Toy Gun Marking	NA
4.31	Balloons	NA
4.32	Certain Toys and Nearly Spherical Ends	NA
4.33	Marbles	NA
4.34	Balls	NA
4.35	Pompoms	NA
4.36	Hemispheric-Shaped Objects	NA
4.37	Yo Yo Elastic Tether Toys	NA
4.38	Magnets	NA
4.39	Jaw Entrapment in Handles and Steering Wheels	NA
4.40	Expanding Materials	NA
4.41	Toy Chest	NA
5	Safety Labeling Requirements	Pass
5.1	Federal Labeling	Pass
5.2	Age Grade Labeling	Pass
5.3	Safety Labeling Requirements	Pass
5.4	Aquatic Toys	NA
5.5	Crib and Playpen Toys	NA
5.6	Mobiles	NA
5.7	Stroller and Carriage Toys	NA
5.8	Toys Intended to be Assembled By an Adult	NA
5.9	Simulated Protective Devices	NA
5.10	Toys with Functional Sharp Edges or Points	NA
5.11	Small Objects, Small Balls, Marbles and Balloons	Pass
5.12	Toys Caps	NA
5.13	Art Materials	NA
5.14	Electric Toy	NA
5.15	Battery-Operated Toys	NA
5.16	Promotional Materials	NA
5.17	Magnets	NA
6	Instructional Literature	Pass
6.1	Definition and Description	Pass
6.2	Crib and Playpen Toys	NA



TEST REPORT

Clause	Description	Result
6.3	Mobiles	NA
6.4	Toys Intended to be Assembled By an Adult	NA
6.5	Battery-Operated Toys	NA
6.6	Battery-powered Ride-on Toys	NA
6.7	Toys in Contact with Food	NA
6.8	Toy Chests	NA
6.9	The instructional material for toys which require a Manufacturer -supplied specialty or custom tool to access the battery(ies) shall direct caregivers to retain the tool for future use, to store it where the child cannot access it, and state that the tool is not a toy.	NA
7.1	Producers Markings	Pass
7.2	Battery-Powered Ride-On Toys	NA
7.3	Toy Chests	NA

B.2 ASTM F963-23: Standard Consumer Safety Specification for toy Safety - Flammability

Sample	Burn rate (in./sec.)	Limit(in./s)	Result
Wooden Kids Playhouse	IBE	0.1	Pass

1. DNI = Did not ignite (no time).
2. NA = Not Applicable
3. IBE = Ignited but self-extinguished before burn-rate could be determined (no time).
4. All styles of the submitted samples (and its accessories) was/were tested, the above result only showed the most severe burn rate of the samples.
5. The burn rate of a composite product (that is solid/fabric combined)exceeds 0.1 in./s in part due to the presence of a permanently attached fabric, then a secondary test to fabric separately was conducted in accordance the standard.



**Dongguan Huanren Lab
Technology Co., Ltd**

All test reports issued by this laboratory are electronically signed using UKEY digital signatures. Reports with missing or damaged e-signatures shall be deemed invalid..

NOTE: IAS is International Accreditation Service. www.iasonline.org

IAS is ILAC/IAF Mutual Recognition Arrangement (MRA) Signatory.

Room 301, Building 2, No. 53 Jinyuan Road, Liaobu Town, Dongguan City, Guangdong Province ,China

Tel: (86-769)13423451083

E-mail:CS@Labsoon.com

<http://www.Labsoon.com>

TEST REPORT

B.3 ASTM F963-23 Section 4.3.5.2(2)(a) Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal) , analyzed by Inductively Coupled Plasma-Optical Emission Spectrometry(ICP-OES).

Item	Unit	MDL	Results				Limit
			4+5+6	7	8+9+10	--	
Lead Content (Pb)	mg/kg	10	ND	ND	ND		100
Conclusion	/	/	Pass				/

Remark:

(1)ND = Not Detected, less than the MDL

(2)MDL= Method Detected Limit

(3)mg/kg = ppm = parts per million

B.4 ASTM F963-23 Section 4.3.5.1(1) Total Lead in Paints and Surface Coatings

Item	Unit	MDL	Results														Limit
			1	2	3	--	--	--	--	--	--	--	--	--	--	--	
Lead Content (Pb)	mg/kg	10	ND	ND	ND												90
Conclusion	/	/	Pass														/

Test Method: CPSC-CH-E-1003-09.1 , analyzed by Inductively Coupled Plasma-Optical Emission Spectrometry(ICP-OES).

Remark:N/A = Not Applicable

ND = Not Detected, less than the MDL

TEST REPORT

B.5.1-ASTM F963-23: Toxicology

- Migration of Certain Elements in Substrate Materials Section 4.3.5.2

Test Item	Lead Pb(M)	Cadmium Cd (M)	Antimony Sb (M)	Barium Ba (M)	Arsenic As (M)	Chromium Cr (M)	Mercury Hg (M)	Selenium Se (M)
Maximum Limit (mg/kg)	Non- Modeling clay materials							
	90	75	60	1000	25	60	60	500
	Modeling clays							
	90	50	60	250	25	25	25	500
MDL (mg/kg)	5	5	5	5	2.5	5	5	5
Test Method/ Instrument	ASTM F963-23/ ICP-OES							

B.5.2-ASTM F963-23 4.3.5.2: Substrate Element Migration Content

Item	Unit	Results			
		4+5+6	7	8+9+10	--
Lead Pb (M)	mg/kg	ND	ND	ND	
Antimony Sb (M)	mg/kg	ND	ND	ND	
Arsenic As (M)	mg/kg	ND	ND	ND	
Barium Ba (M)	mg/kg	ND	ND	ND	
Cadmium Cd (M)	mg/kg	ND	ND	ND	
Chromium Cr (M)	mg/kg	ND	ND	ND	
Mercury Hg (M)	mg/kg	ND	ND	ND	
Selenium Se (M)	mg/kg	ND	ND	ND	
Conclusion	/	Pass			

Remark:

(1)ND = Not Detected, less than the MDL

(2)MDL= Method Detected Limit

(3)mg/kg = ppm = parts per million



**Dongguan Huanren Lab
Technology Co., Ltd**

All test reports issued by this laboratory are electronically signed using UKEY digital signatures. Reports with missing or damaged e-signatures shall be deemed invalid..

NOTE: IAS is International Accreditation Service. www.iasonline.org

IAS is ILAC/IAF Mutual Recognition Arrangement (MRA) Signatory.

Room 301, Building 2, No. 53 Jinyuan Road, Liaobu Town, Dongguan City, Guangdong Province ,China

Tel: (86-769)13423451083

E-mail:CS@Labsoon.com

<http://www.Labsoon.com>

TEST REPORT

B.6 ASTM F963-23 4.3.5.1(2): Coating Element Migration Content

Item	Unit	Results														
		1	2	3	--	--	--	--	--	--	--	--	--	--	--	--
Lead Pb (M)	mg/kg	ND	ND	ND												
Antimony Sb (M)	mg/kg	ND	ND	ND												
Arsenic As (M)	mg/kg	ND	ND	ND												
Barium Ba (M)	mg/kg	ND	ND	ND												
Cadmium Cd (M)	mg/kg	ND	ND	ND												
Chromium Cr (M)	mg/kg	ND	ND	ND												
Mercury Hg (M)	mg/kg	ND	ND	ND												
Selenium Se (M)	mg/kg	ND	ND	ND												
Conclusion	/	Pass														

Remark:N/A = Not Applicable, ND = Not Detected, less than the MDL

TEST REPORT

B.7 ASTM F963-23 Section 4.3.8 Phthalates Content

Test Method: CPSC-CH-C1001-09.4, analyzed by Gas Chromatography with Mass Spectrometry(GC-MS).

Item	CAS No.	Unit	MDL	Results		Limit
				1+2+3	4+5+6	
Dibutyl phthalate (DBP)	84-74-2	mg/kg	50	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	mg/kg	50	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	mg/kg	50	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	mg/kg	50	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	mg/kg	50	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	50	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	50	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	mg/kg	50	ND	ND	1000
Conclusion	/	/	/	Pass		/

Item	CAS No.	Unit	MDL	Results		Limit
				7	--	
Dibutyl phthalate (DBP)	84-74-2	mg/kg	50	ND		1000
Benzyl butyl phthalate (BBP)	85-68-7	mg/kg	50	ND		1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	mg/kg	50	ND		1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	mg/kg	50	ND		1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	mg/kg	50	ND		1000
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	50	ND		1000
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	50	ND		1000
Di-n-pentyl phthalate (DPENP)	131-18-0	mg/kg	50	ND		1000
Conclusion	/	/	/	Pass		/

Remark:

(1)ND = Not Detected, less than the MDL(2)MDL= Method Detected Limit(3)mg/kg = ppm = parts per million



**Dongguan Huanren Lab
Technology Co., Ltd**

All test reports issued by this laboratory are electronically signed using UKEY digital signatures. Reports with missing or damaged e-signatures shall be deemed invalid..

NOTE: IAS is International Accreditation Service. www.iasonline.org

IAS is ILAC/IAF Mutual Recognition Arrangement (MRA) Signatory.

Room 301, Building 2, No. 53 Jinyuan Road, Liaobu Town, Dongguan City, Guangdong Province ,China

Tel: (86-769)13423451083

E-mail:CS@Labsoon.com

<http://www.Labsoon.com>

TEST REPORT

C.1 CPSIA Section 101.(a), Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.2 (Metal), CPSC-CH-E1002-08.2 (Non-Metal) , analyzed by Inductively Coupled Plasma-Optical Emission Spectrometry(ICP-OES).

Item	Unit	MDL	Results				Limit
			4+5+6	7	8+9+10	--	
Lead Content (Pb)	mg/kg	10	ND	ND	ND		100
Conclusion	/	/	Pass				/

Remark:

(1)ND = Not Detected, less than the MDL

(2)MDL= Method Detected Limit

(3)mg/kg = ppm = parts per million



**Dongguan Huanren Lab
Technology Co., Ltd**

All test reports issued by this laboratory are electronically signed using UKEY digital signatures. Reports with missing or damaged e-signatures shall be deemed invalid..

NOTE: IAS is International Accreditation Service. www.iasonline.org

IAS is ILAC/IAF Mutual Recognition Arrangement (MRA) Signatory.

Room 301, Building 2, No. 53 Jinyuan Road, Liaobu Town, Dongguan City, Guangdong Province ,China

Tel: (86-769)13423451083

E-mail:CS@Labsoon.com

<http://www.Labsoon.com>

TEST REPORT

C.2 CPSIA Section 101.(f), Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E-1003-09.1 analyzed by Inductively Coupled Plasma-Optical Emission Spectrometry(ICP-OES).

Item	Unit	MDL	Results														Limit
			1	2	3	--	--	--	--	--	--	--	--	--	--	--	
Lead Content (Pb)	mg/kg	10	ND	ND	ND												90
Conclusion	/	/	Pass														/

Remark: N/A = Not Applicable

ND = Not Detected, less than the MDL

TEST REPORT

C.3 CPSIA Section 108, Determination of Phthalates

Test Method: CPSC-CH-C1001-09.4, analyzed by Gas Chromatography with Mass Spectrometry(GC-MS).

Item	CAS No.	Unit	MDL	Results		Limit
				1+2+3	4+5+6	
Dibutyl phthalate (DBP)	84-74-2	mg/kg	50	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	mg/kg	50	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	mg/kg	50	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	mg/kg	50	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	mg/kg	50	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	50	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	50	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	mg/kg	50	ND	ND	1000
Conclusion	/	/	/	Pass		/

Item	CAS No.	Unit	MDL	Results		Limit
				7	--	
Dibutyl phthalate (DBP)	84-74-2	mg/kg	50	ND		1000
Benzyl butyl phthalate (BBP)	85-68-7	mg/kg	50	ND		1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	mg/kg	50	ND		1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	mg/kg	50	ND		1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	mg/kg	50	ND		1000
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	50	ND		1000
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	50	ND		1000
Di-n-pentyl phthalate (DPENP)	131-18-0	mg/kg	50	ND		1000
Conclusion	/	/	/	Pass		/

Remark:

(1)ND = Not Detected, less than the MDL

(2)MDL= Method Detected Limit

(3)mg/kg = ppm = parts per million



**Dongguan Huanren Lab
Technology Co., Ltd**

All test reports issued by this laboratory are electronically signed using UKEY digital signatures. Reports with missing or damaged e-signatures shall be deemed invalid..

NOTE: IAS is International Accreditation Service. www.iasonline.org

IAS is ILAC/IAF Mutual Recognition Arrangement (MRA) Signatory.

Room 301, Building 2, No. 53 Jinyuan Road, Liaobu Town, Dongguan City, Guangdong Province ,China

Tel: (86-769)13423451083

E-mail:CS@Labsoon.com

<http://www.Labsoon.com>

TEST REPORT

C.4 CPSIA Sec.103 Tracking Labels for Children's Products/15 U.S. Code § 2063(a)(5)

Description	Result
a) Is the product intended for children under 12 years? If no, the section is not applicable.	Pass
b) Is the product under the exemption of marking on children's product?	N/A
1.Product is too small to be marked.	N/A
2.Products stay with or be contained in their original packaging.	N/A
3.Product is sold through a bulk vending machine.	N/A
4.Physical mark would weaken or damage the product or impair its utility.	N/A
5.Product surface would be impossible to mark permanently.	N/A
6.Aesthetics of the product would be ruined by a mark.	N/A
c) Is the product and packaging or only packaging (for product exempted from the marking) marked below information?	Pass
Name of the manufacturer or the name of the private labeler.	Pass
Manufacturer or private labeler location, including the name of the country, and the name or other means of coding of city and state.	Pass
3) Date of production of the product, in a form of MM/YY or any other coding system.	Pass
4) Cohort information (including the batch, run number, or another identifying characteristic).	Pass
d) Is the label permanent after below permanency testing?	Pass

TEST REPORT

D. Tracking labels for children's products

Product Label	
Sample Name	Wooden Kids Playhouse
Sample Description	/
Model No.	W2644P368997
Trade marks	/
Manufacturer	FUZHOU HC HOME CO., LTD
Address	RM 203, Building 47, Gongjiao Courtyard, No.1 Sheng Fu Road, Gulou District, Fuzhou, Fujian, China
Age grading	3-10 years old
ASIN	/
Batch No.	250812
Production date	Aug.01,2025
Address of production	RM 203, Building 47, Gongjiao Courtyard, No.1 Sheng Fu Road, Gulou District, Fuzhou, Fujian, China
 WARNING:CHOKING HAZARD -Small Parts.Not for children under 3 years.	

TEST REPORT

The submitted sample was tested under the following requirements requested by the applicant, subject to the information stated in the remark and attached page(s) for details.

Sample Information:

Description&Photo of the submitted sample :


Coating samples		
ID.	Description	
1	Blue	Coating
2	Brown	Coating
3	Grey	Coating

Substrate samples		
ID.	Description	
4	Beige	Wood
5	Black	Plastic
6	Green	Plastic
7	Grey	Plastic
8	Silver	Metal
9	Gold	Metal



Coating samples		
ID.	Description	

Substrate samples		
ID.	Description	
10	Black	Metal


		
--	--	--

Remark:

1.The tested parts were designated by client.


TEST REPORT

Test Product Photo(s):



TEST REPORT

Test Product Photo(s):



(End of report)

TEST REPORT

STATEMENT

- 1.This report is considered invalid without approved signature, Detection special seal or Report seal;
2. The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which HRL hasn't verified;
3. The result(s) shown in this report refer(s) only to the sample(s) tested;
4. In case of any discrepancy between the English version and Chinese version of the testing reports(if generated),the Chinese version shall prevail.
5. When the report without qualification seal, the testing data and result(s) in this reports(are) just for scientific research, education, internal quality control and product development etc.
- 6.Unless otherwise specified, refer to ILAc-G8:09/2019 and use the binary decision rule of simple acceptance (W=0) for conformity assessment.
- 7.This test report is issued by the company subject to its General Conditions of Services printed overleaf or available on request and accessible at www.Labsoon.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this report refer only to the sample(s) tested. Without prior written permission of the company, this test report cannot be reproduced, except in full.

