



Four largest Rq failures in full-cohort LOO (reported without cherry-picking)


6099 RHEED key frame




generated AFM
Rq=4.64 nm, FSMI=2.68 nm, C=6/100




measured AFM
Rq=10.32 nm, FSMI=9.32 nm




6095 RHEED key frame




generated AFM
Rq=4.90 nm, FSMI=3.70 nm, C=22/100




measured AFM
Rq=9.87 nm, FSMI=8.57 nm




6063 RHEED key frame




generated AFM
Rq=3.01 nm, FSMI=1.79 nm, C=65/100




measured AFM
Rq=5.87 nm, FSMI=4.88 nm



6090 RHEED key frame



generated AFM
Rq=7.06 nm, FSMI=6.05 nm, C=4/100



measured AFM
Rq=4.69 nm, FSMI=3.17 nm

