



# Four largest Sq failures in full-cohort LOO (reported without cherry-picking)


6099 RHEED key frame




generated AFM  
predicted Sq=5.05 nm; FSMI=4.30 nm  
C=10/100




measured AFM  
displayed scan Sq=9.39 nm  
sample median Sq=9.39 ± 0.21 nm (IQR)




6095 RHEED key frame




generated AFM  
predicted Sq=4.86 nm; FSMI=4.42 nm  
C=14/100




measured AFM  
displayed scan Sq=9.07 nm  
sample median Sq=9.07 ± 2.19 nm (IQR)




6057 RHEED key frame




generated AFM  
predicted Sq=0.97 nm; FSMI=0.86 nm  
C=82/100




measured AFM  
displayed scan Sq=3.95 nm  
sample median Sq=3.95 ± 0.19 nm (IQR)



6081 RHEED key frame



generated AFM  
predicted Sq=3.56 nm; FSMI=3.15 nm  
C=29/100



measured AFM  
displayed scan Sq=0.94 nm  
sample median Sq=0.94 ± 0.03 nm (IQR)

