



AFM candidate scans: sample 6057


GdSb_N6057_ctr_020
Rq=4.9 nm; $1 \times 1 \mu\text{m}$




GdSb_N6057_ctr_015
Rq=4.9 nm; $1 \times 1 \mu\text{m}$




GdSb_N6057_ctr_017
Rq=5.2 nm; $1 \times 1 \mu\text{m}$




GdSb_N6057_edge_019
Rq=5.3 nm; $1 \times 1 \mu\text{m}$



GdSb_N6057_ctr_016
Rq=5.4 nm; $1 \times 1 \mu\text{m}$



GdSb_N6057_edge_018
Rq=5.5 nm; $1 \times 1 \mu\text{m}$



GdSb_N6057_edge_014
Rq=6.5 nm; $1 \times 1 \mu\text{m}$

