



RHEED 6072 (train)
condition conf 14; morphology conf 69/100



M10 generated
Rq=2.44 nm




Measured AFM
Rq=1.47 nm; shared z=[-5.3, 4.9] nm




RHEED 6022 (val)
condition conf 16; morphology conf 50/100



M10 generated
Rq=2.48 nm




Measured AFM
Rq=1.65 nm; shared z=[-5.3, 5.7] nm




RHEED 6082 (train)
condition conf 19; morphology conf 38/100




M10 generated
Rq=2.60 nm




Measured AFM
Rq=1.86 nm; shared z=[-5.1, 6.0] nm




RHEED 6084 (train)
condition conf 18; morphology conf 50/100



M10 generated
Rq=2.84 nm




Measured AFM
Rq=2.01 nm; shared z=[-5.4, 6.6] nm




RHEED 6078 (train)
condition conf 17; morphology conf 94/100



M10 generated
Rq=2.66 nm




Measured AFM
Rq=2.11 nm; shared z=[-5.3, 6.5] nm



RHEED 6048 (train)
condition conf 15; morphology conf 62/100



M10 generated
Rq=2.54 nm



Measured AFM
Rq=2.55 nm; shared z=[-6.1, 6.2] nm

