



Four largest Sq failures in full-cohort LOO (reported without cherry-picking)


6099 RHEED key frame




generated AFM
predicted Sq=5.52 nm; FSMI=4.01 nm
C=29/100




measured AFM
displayed scan Sq=9.39 nm
sample median Sq=9.39 ± 0.21 nm (IQR)




6062 RHEED key frame




generated AFM
predicted Sq=6.17 nm; FSMI=4.21 nm
C=14/100




measured AFM
displayed scan Sq=3.18 nm
sample median Sq=3.09 ± 0.25 nm (IQR)




6057 RHEED key frame




generated AFM
predicted Sq=1.01 nm; FSMI=0.92 nm
C=100/100




measured AFM
displayed scan Sq=3.95 nm
sample median Sq=3.95 ± 0.19 nm (IQR)



6090 RHEED key frame



generated AFM
predicted Sq=5.13 nm; FSMI=3.87 nm
C=36/100



measured AFM
displayed scan Sq=2.41 nm
sample median Sq=2.41 ± 0.06 nm (IQR)

