



RHEED keyframe, five upper-left 1 μm AFM ground truths, and retrained A3 retrieval


N6342 RHEED keyframe




Ground truth 1
Rq = 0.74 nm




Ground truth 2
Rq = 0.93 nm




Ground truth 3
Rq = 0.92 nm




Ground truth 4
Rq = 0.88 nm




Ground truth 5
Rq = 0.88 nm




Retrieved
Pred 1.45; GT T4 0.89 nm
Rq = 1.45 nm




N6389 RHEED keyframe




Ground truth 1
Rq = 2.36 nm




Ground truth 2
Rq = 2.16 nm




Ground truth 3
Rq = 2.54 nm




Ground truth 4
Rq = 2.37 nm




Ground truth 5
Rq = 2.28 nm




Retrieved
Pred 2.52; GT T4 2.34 nm
Rq = 2.52 nm




N6390 RHEED keyframe




Ground truth 1
Rq = 2.40 nm




Ground truth 2
Rq = 2.36 nm




Ground truth 3
Rq = 2.29 nm



Ground truth 4
Rq = 2.25 nm



Ground truth 5
Rq = 2.15 nm



Retrieved
Pred 2.25; GT T4 2.30 nm
Rq = 2.25 nm

