



Four largest Sq failures in full-cohort LOO (reported without cherry-picking)


6095 RHEED key frame




generated AFM
predicted Sq=4.67 nm; FSMI=4.31 nm
C=18/100




measured AFM
displayed scan Sq=9.07 nm
sample median Sq=9.07 ± 2.19 nm (IQR)




6099 RHEED key frame




generated AFM
predicted Sq=5.24 nm; FSMI=4.45 nm
C=10/100




measured AFM
displayed scan Sq=9.39 nm
sample median Sq=9.39 ± 0.21 nm (IQR)




6057 RHEED key frame




generated AFM
predicted Sq=0.79 nm; FSMI=0.70 nm
C=76/100




measured AFM
displayed scan Sq=3.95 nm
sample median Sq=3.95 ± 0.19 nm (IQR)



6081 RHEED key frame



generated AFM
predicted Sq=3.79 nm; FSMI=3.36 nm
C=29/100



measured AFM
displayed scan Sq=0.94 nm
sample median Sq=0.94 ± 0.03 nm (IQR)

