

## TEST REPORT

Report No.: 53686

Date : 30/09/2022

Customer Ref.: DDT N°396

Laboratory Ref.: 220957

Customer(#):

**EMMEGI ZINCATURA SRL**

via Enrico da Fiume 16

33080 FIUME VENETO

IT

PN

Test Requested: ADHESION TEST

Sample Descr. (#): UNALLOYED ZINC COATED PART CODE 17825040000+KTL - BASE MAT. S420MC 4 mm THK-3 WELDING COMPONENTS  
VW 13750-OfI x632

Sampling: Performed by the customer

Date of receipt: 04/08/2022

Date of testing: Start: 29/09/2022 End: 30/09/2022

Test Method: ISO 2409:2020 ISO 2178:2016

Ref. Documents: VW 227:2016

## ADHESION TEST

### TEST DATA

Test method Cross cut

Test temperature 25±5 °C

Adhesive strip TESA 4657

### RESULTS

COATING THICKNESS = 30±5 µm

RATING <1

NS= Not Specified / NA= Not Applicable

[www.dilandrolab.it](http://www.dilandrolab.it)

#: Data provided by the customer. The laboratory disclaims all responsibility for the information provided by the customer.  
Unless otherwise required by standards and technical specifications or agreed with the customer, statements of conformity based on the comparison between results and reference values are reported without taking into account the uncertainty of measurement.  
In the case of sampling performed by the customer, the results reported in this test report apply to the sample as received.  
The results reported in this test report refer only to the tested sample.  
This test report cannot be partially reproduced without a written approval of the laboratory.

Digitally signed by:


**Dr. Umberto Di Landro**

Laboratory Manager

## TEST REPORT

**Report N°:** 53686

**Date:** 30/09/2022



CROSS CUT PHOTO