

## TEST REPORT

**Report No.:** 60709

**Date :** 16/12/2023

**Customer Ref.:** DDT N°568

**Laboratory Ref.:** 231527

Customer(#):

**EMMEGI ZINCATURA SRL**

via Enrico da Fiume 16

33080 FIUME VENETO

IT

PN

**Test Requested:** ADHESION TEST

**Sample Descr. (#):** MALE AND FEMALE BALL STUD

**Sampling:** Performed by the customer

**Date of receipt:** 05/12/2023

**Date of testing:** Start: 06/12/2023 End: 15/12/2023

**Test Method:** ISO 2819:2017

## ADHESION TEST

**TEST DESCRIPTION** - THE SAMPLES ARE STORED AT  $220 \pm 10$  °C FOR 30 MINUTES, THAN ARE QUENCHED IN WATER AT  $20 \pm 5$  °C

**RESULTS** - NO VISIBLE DEFECTS DETECTED

NS= Not Specified / NA= Not Applicable

[www.dilandrolab.it](http://www.dilandrolab.it)

#: Data provided by the customer. The laboratory disclaims all responsibility for the information provided by the customer.  
Unless otherwise required by standards and technical specifications or agreed with the customer, statements of conformity based on the comparison between results and reference values are reported without taking into account the uncertainty of measurement.  
In the case of sampling performed by the customer, the results reported in this test report apply to the sample as received.  
The results reported in this test report refer only to the tested sample.  
This test report cannot be partially reproduced without a written approval of the laboratory.

Digitally signed by:

**Dr. Umberto Di Landro**

Laboratory Manager

## TEST REPORT

Report N°: 60709

Date: 16/12/2023



SAMPLES AT THE END TEST