



# THICKNESS TEST



Measuring Instrument

FISCHERSCOPE X-RAY

Fiume Veneto, 01/03/2022

<i>Customer</i>	SWG
<i>Ref. Your Bill</i>	220111
<i>Our Ref. Bill</i>	
<i>Order Number</i>	202103973
<i>Article Code</i>	190 60 160 01RW40171 07342
<i>Article Description</i>	ASSY 4 – SeFRT – RW40 – SF – 34 “Grobgang-T-blvz A3K
<i>Surface Treatment</i>	Galvanized, blue passivated and sliding coated in concentration 1:3
<i>Standard Ref.</i>	
<i>Reference Value Zn (<math>\mu</math>)</i>	8 - 12
<i>Result</i>	POSITIVE

## RILEVAZIONE

Result

<i>Measures</i>	10
<i>Average</i>	10,70
<i>Minimum</i>	8,51
<i>Maximum</i>	13,20

<i>N = 1</i>	8,51
<i>N = 2</i>	9,58
<i>N = 3</i>	11,60
<i>N = 4</i>	13,20
<i>N = 5</i>	10,50
<i>N = 6</i>	10,10
<i>N = 7</i>	10,70
<i>N = 8</i>	9,80
<i>N = 9</i>	12,70
<i>N = 10</i>	10,10

Il tecnico di Laboratorio  
Laboratory Technician