

TEST REPORT

Report No.: 53711

Date : 05/09/2022

Customer Ref. (#): DDT N°396

Laboratory Ref.: 220956

Customer(#):

EMMEGI ZINCATURA SRL

via Enrico da Fiume 16

33080 FIUME VENETO

IT

PN

Test Requested: ZINC COATING THICKNESS MEASUREMENT

Sample Descr. (#): UNALLOYED ZINC COATED PART CODE 17825050000 - BASE MAT. S420MC 4 mm THK-3 WELDING COMPONENTS
VW13750 OfI c310

Sampling: Performed by the customer

Date of receipt: 04/08/2022

Date of testing: Start: 05/09/2022 End: 05/09/2022

Test Method: ISO 2178:2016

Ref. Documents: VW TL217:2009-08 p.3.7

ZINC COATING THICKNESS MEASUREMENT

Sample ID (#): **CODE 17825050000**

Test	Unit	Result
Coating thickness	µm	12

Note: COMPLIANCE TO TL217:2009 SPECIFICATION

End of test report

Note: Compliant with VW TL217:2016-12
Date: 06/04/2023
Simone Di Landro



NS= Not Specified / NA= Not Applicable

www.dilandrolab.it

#: Data provided by the customer. The laboratory disclaims all responsibility for the information provided by the customer. Unless otherwise required by standards and technical specifications or agreed with the customer, statements of conformity based on the comparison between results and reference values are reported without taking into account the uncertainty of measurement. In the case of sampling performed by the customer, the results reported in this test report apply to the sample as received. The results reported in this test report refer only to the tested sample. This test report cannot be partially reproduced without a written approval of the laboratory.

Digitally signed by:

Dr. Umberto Di Landro

Laboratory Manager