# **BMW Group**

Technologie Werkstoff- und Verfahrensanalytik

# Kurzbewitterung im Xenontestgerät Farbbeständigkeit

Accelerated weathering colour stability

**AA-0236** Seite **1** von **4** 

#### 1 Zweck

Die Prüfung dient der Simulation von Bewitterungseinflüssen, die in der Praxis an der Fahrzeugoberfläche auftreten, unter Verwendung von Xenontestgeräten mit Zeitraffereffekt.

# 2 Geltungsbereich

Diese Arbeitsanweisung gilt für die BMW Group Technologie Werkstoff- und Verfahrensanalytik, Prozesspartner und Lieferanten weltweit.

# 3 Ablaufregelung und Zuständigkeiten

#### 3.1 Begriffe

Abkürzungserklärungen sind über einen entsprechenden Link auf der Qualitäts-Homepage der Technologie Werkstoff- und Verfahrensanalytik abrufbar.

# 3.2 Probenvorkonditionierung

Die Proben sind vor der Prüfung min. 24 h bei Raumtemperatur oder nach speziellen Anforderungen an die jeweiligen Materialien zu lagern.

#### 3.3 Geräte und Hilfsmittel

Siehe DIN EN ISO 4892-2 Punkt 4 (Verfahren A, Tabelle 1)

# 3.4 Durchführung der Prüfung

Die Prüfung erfolgt nach DIN EN ISO 4892-2 Punkt 6.3 Tabelle3 (Verfahren A) Zyklus 1. Die Prüfzeit ist der jeweiligen Materialanforderung (z.B. BMW Group Standard) zu entnehmen.

# 4 Auswertung der Ergebnisse, Dokumentation

Die Auswertung kann visuell oder messtechnisch erfolgen.

Visuell:

Die visuelle Auswertung erfolgt nach DIN EN ISO 4628 -1

Messtechnisch:

Die messtechnische Auswertung erfolgt bei Bedarf für Glanz nach AA-0101 und für Farbton nach AA-0354.

Bei Mehrschichtaufbauten sollte abschließend zusätzlich die Haftung durch Gitterschnittprüfung nach AA-0180 überprüft werden.

Verfasser / Dokumentenverantwortlicher:Prüfer:Freigeber:gez.gez.gez.Patrizia DegenChristoph StinnerClaudia Stephan

# 5 Wartung und Kalibrierung

Wird im iPMa der BMW-Group geregelt bzw. eigenverantwortlich durch den Lieferanten.

# 6 Reparatur

Reparaturen werden in der Regel vom Service-Dienst des Herstellers ausgeführt und durch Tätigkeitsnachweis belegt.

# 7 Umwelt- und Arbeitsschutz

Die geltenden Bestimmungen für Umweltschutz, Arbeitssicherheit, Ergonomie und Gesundheitsschutz in der BMW Group sind einzuhalten.

# 8 Mitgeltende Unterlagen, Anlagen

DIN EN ISO 4892-2 DIN EN ISO 4628 AA-0101 AA-0354 AA-0180

# 9 Änderungsdokumentation

| Index | Anlass  | Ausgabe-Datum  |
|-------|---|----------------|
| ,,"   | Erstausgabe<br>Vormals AA-P 288 (06/2006<br>Erstausgabe)  | November 2010  |
| а     | <ul><li>3.3 Verfahren eingefügt</li><li>3.4 Verfahren eingefügt</li><li>4 Gitterschnitt-AA-Nr. berichtigt</li></ul>                           | September 2014 |
| b     | Umstellung auf Technologie Werkstoff- und<br>Verfahrensanalytik<br>War: Labortechnik<br>Pkt. 4: Bewertung erfolgt alle 500h wurde<br>entfernt | März 2017      |

#### 10 Verteiler

MPM DMS, entsprechend UAA 4.4.6/01

**BMW Group** 

Technology Material and Process Analysis

# Accelerated weathering colour stability

Kurzbewitterung im Xenontestgerät Farbbeständigkeit **AA-0236** Page **3** of **4** 

#### 1 Purpose

This test instruction describes the test procedure for simulate weathering impact, on all substrates being used for exterior body or hang-on parts on a vehicle, under using accelerated weathering with time-lapse.

# 2 Scope of Application

This work instruction is valid for the BMW Group Technology Material and Process Analysis, Process Partners and Suppliers worldwide.

# 3 Procedure and Responsibilities

#### 3.1 Terms

Explanation of abbreviations is available using the corresponding link on the Quality Homepage of the Technology Material and Process Analysis

#### 3.2 Preconditioning

Before testing, the samples will conditioning 24h by room temperature or if necessary special needs on respective materials.

#### 3.3 Equipment and facilities

See DIN EN ISO 4892-2 point 4 (Method A, Tab 1)

#### 3.4 lead through of testing

The testing does take about DIN EN ISO 4892-2 point 6.3 table 3, Method A, circle 1 The testing time special needs on respective materials (e.g. BMW Group Standard).

# 4 Evaluation of Test Results, Documentation

The interpretation can be visual or measurement.

Vigual<sup>,</sup>

The visual interpretation will made by DIN EN ISO 4628

Measurement:

The measurement interpretation

(brightness) will made by AA-0101,

(colour) will made by AA-0354

By multy-layer-assembly concluding will accessory checked the Cross hedge by AA-0180.

Author / Document Owner: Verifier: Release Owner: signed signed signed

Patrizia Fuchs Christoph Stinner Claudia Stephan

# 5 Maintenance and Calibration

According to BMW Group iPMa. Suppliers are individually responsible

# 6 Repair

Repairs are usually performed by the service department of the equipment manufacturer and documented by an activity report.

# 7 Environmental and Industrial Safety

The regulations for health & safety, environmental protection and ergonomics of the BMW Group have to be followed.

# 8 Applicable Documents

DIN EN ISO 4892-2 DIN EN ISO 4628 AA-0101 AA-0354 AA-0180

#### 9 Revisions

| Revision | Note   | Date           |
|----------|--|----------------|
| ,,"      | First issued<br>Was AA-P 288 (06/2009 first issue)   | November 2010  |
| а        | 3.3 Method included<br>3.4 Method included<br>4 cross hedge-AA-number amended  | September 2014 |
| b        | Change to Technology Material and Process<br>Analysis, last name: Labortechnik<br>Point 4: The assessment value is doing all<br>500h is delete | March 2017     |

#### 10 Distribution

MPM DMS, according to UAA 4.4.6/01