





LAB Nº 1617 L

16/12/2023

PΝ

LABORATORIO CHIMICO DI LANDRO SAS - Via A. Toscanini 18 - 26013 - CREMA - CR - Italy - Phone: +39 0373-202906 - VAT N. IT01231610195 - info@dilandrolab.it

TEST REPORT

RdP N.: 60638

Date:

Customer (#):

EMMEGI ZINCATURA SRL

via Enrico da Fiume 16

33080 FIUME VENETO

IT

Test Requested: SALT SPRAY CORROSION TESTING

DDT N.568

231526

Sample Descr. (#): MALE & FEMALE BALL STUDS

Sampling: Performed by the customer

Date of receipt: 06/12/2023

Customer Ref. (#):

Laboratory Ref.:

Date of testing: Start: 06/12/2023 End: 16/12/2023

SALT SPRAY CORROSION TESTING

Test Method:	ISO 9227:2022
Ref. Documents:	1
Test period:	240h
Solution:	50 ± 5 g/l NaCl (> 99,5%) in deionized water (Cond.< 20 μS/cm)
Temperature:	35°C ± 2 °C
Solution pH	7
Solution density:	1,029 - 1,036 g/ml
Collection rate:	1,5 ± 0,5 ml/h
Acceptance criteria:	NO WHITE RUST

Note:

NS= Not Specified / NA= Not Applicable / \ast = Not accredited by Accredia

www.dilandrolab.it

#: Data provided by the customer. The laboratory disclaims all responsibility for the information provided by the customer.

Unless otherwise required by standards and technical specifications or agreed with the customer, statements of conformity based on the comparison between results and reference values are reported without taking into account the uncertainty of measurement. In the case of sampling performed by the customer, the results reported in this test report apply to the sample as received. The results reported in this test report refer only to the tested sample.

This test report cannot be partially reproduced without a written approval of the laboratory.

Digitally signed by:

Dr. Umberto Di Landro

Laboratory Manager







LAB Nº 1617 L

LABORATORIO CHIMICO DI LANDRO SAS - Via A. Toscanini 18 - 26013 - CREMA - CR - Italy - Phone: +39 0373-202906 - VAT N. IT01231610195 - info@dilandrolab.it

TEST REPORT

RdP N.: 60638

Date: 16/12/2023

RESULTS:

Sample Id (#): Zn/Ni COATED SAMPLES

Date:	Period (h):	Evaluation:
06/12/2023	0	START TEST
16/12/2023	240	PRESENCE OF LIGHT WHITE RUST

NS= Not Specified / NA= Not Applicable / * = Not accredited by Accredia

www.dilandrolab.it

#: Data provided by the customer. The laboratory disclaims all responsibility for the information provided by the customer.

Unless otherwise required by standards and technical specifications or agreed with the customer, statements of conformity based on the comparison between results and reference values are reported without taking into account the uncertainty of measurement. In the case of sampling performed by the customer, the results reported in this test report apply to the sample as received.

The results reported in this test report refer only to the tested sample.

This test report cannot be partially reproduced without a written approval of the laboratory.

Digitally signed by:

Dr. Umberto Di Landro

Laboratory Manager







LAB N° 1617 L

LABORATORIO CHIMICO DI LANDRO SAS - Via A. Toscanini 18 - 26013 CREMA - CR - Italy - Phone: +39 0373-202906 - VAT N. IT01231610195 - info@dilandrolab.it

TEST REPORT

Report No.: 60638 **Date:** 16/12/2023



SAMPLE AT THE END TEST