

## **Linear Low Density Polyethylene** Aramco LLDPE F2111

## **Product Description**

Aramco LLDPE F2111 is a linear low density polyethylene resin and is typically used for blown film applications. Films made from this resin typically exhibits good optical properties, impact strength and tensile properties.

This product does not contain slip and anti-blocking agents.

## **Typical Applications**

General purpose film, lamination film, stretch film

This product is not intended for use in medical and pharmaceutical applications.

Physical Properties		Unit	Test Method	Value <sup>(1)</sup>
Melt Flow Index (190°C/2.16kg)		g/10min	ASTM D1238	1.1
Density		g/cm³	ASTM D792 Method A	0.921
Melting Point		°C	DSC	122
Film Properties <sup>(2)</sup>				
Tensile Strength at Break	MD	MPa	ASTM D882	35
	TD			30
Tensile Elongation at Break	MD	%	ASTM D882	740
	TD			840
1% Secant Modulus	MD	MPa	ASTM D882	205
	TD			250
Elmendorf Tear Strength	MD	mN	ASTM D1922	1330
	TD			3940
Dart Drop Impact		g	ASTM D1709	115
Haze		%	ADTM D1003	7
Gloss (45°)			ASTM D2457	80

<sup>(1)</sup> Typical values only, not to be construed as specification limits

Processing conditions: Recommended melt temperature: 180 – 200 °C

Storage and handling: Aramco LLDPE F2111 should be stored in a dry cool place with adequate ventilation and protected from UV-light at temperature below 50 °C

Food Contact and other Regulations: Aramco LLDPE F2111 resin is suitable for food contact applications. Detailed information is provided in Material Safety Datasheet and for additional specific information, please contact Saudi Aramco Products Trading Company for certificates.

Saudi Aramco: Company General Use

Disclaimer: © Saudi Aramco Products Trading Company. All information supplied by or on behalf Saudi Aramco Products Trading Company in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Saudi Aramco Products Trading Company assumes no liability whatsoever in respect of application, processing or use made of the provided information or products, or any consequence thereof. The user is solely responsible and liable with respect to the application, processing or use of the provided information or product, shall be verified, or any consequence thereof. No liability whatsoever shall altact has Saudi Aramco Products Trading Company for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the provided information or products by the user. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers and other information.

<sup>(2)</sup>Blown film fabrication conditions: Extruder 55mmφ, Die 125mmφ, Die Gap 2 mm, Temperature 200°C, Output 30kg/h, Blow-up ratio 2.0:1, Thickness 30μm