



中国 · 江西省新余市冶金路1号 邮编:338001
No. 1 YEJIN ROAD, XINYU CITY, JIANGXI PROVINCE, CHINA
POST CODE:338001
TEL: +86 0790-6295805

新余钢铁股份有限公司
XINYU IRON & STEEL CO.,LTD.
产品质量证明书
INSPECTION CERTIFICATE



承压设备用规定温度性能的非合金钢和合金钢板

订货单位 CUSTOMER	无锡市云海钢贸有限公司	产品名称 PRODUCT	GB/T713.2-2023	明细号 DELTAIL NO.	HB24-23850	证明书编号 CERTIFICATE NO.	HB124X1 56849
收货单位 PURCHASER	无锡储运有限公司铁路运输分公司 云海新库	标准 SPECIFICATION	GB/T713.2-2023	交货状态(2) STATE OF DELIVERY	N	签发日期 DATE OF ISSUE	2024-11-10
合同号 CONTRACT NO.	W112024090132	许可证号 LICENSE NO.		车号 TRAIN NO.	1799908	发货日期 DATE OF DELIVERY	2024-11-09

CONTRACT NO.			W112024090132			LICENSE NO.			尺寸及重量 MATERIAL DESCRIPTION										化学成分 CHEMICAL COMPOSITION %									
序号	批号 ROLL NO.	炉号 HEAT NO.	牌号 STEEL GRADE	厚度 THICK			数量 QTY	重量 WEIGHT 吨 MT	分析 区分 (1)	C	Si	Mn	P	S	Cr	Ni	Cu	Nb	V	Ti	Al t	Mo						
				mm	宽度 WIDTH	长度 LENGTH																						
NO				34	2500	11000	1	7.448	L	0.18	0.28	1.42	0.021	0.003	0.07	0.03	0.05	0.001	0.004	0.012	0.036	0.01						
1√	H2453401	J41-10893A	Q345R							0.44	0.020	0.16																
2√	H2453410	J41-10893A	Q345R	34	2500	11000	2	14.896	L	0.18	0.28	1.42	0.021	0.003	0.07	0.03	0.05	0.001	0.004	0.012	0.036	0.01						
										0.44	0.020	0.16																

序号 NO	批号 ROLL NO.	试验区分 (3)	拉伸试验 TENSILE TEST			冲击试验 IMPACT TEST			探伤 U.T (8)	合格 PASS	产品类型 PRODUCT	正品
			位置 方向 (4)	温度 T	屈服 Y.S ReL	抗拉 T.S Rm	伸长率 E.L %	位置 方向 (4)	温度 T			
1	H2453401	H	T	室温	406	560	28.0	T	A	合格	合格	合格
2	H2453410	H	T	室温	392	561	26.5	T	A	合格	合格	合格

外观及尺寸 ACCEPTABLE VISUAL AND DIMENSIONS										合格 PASS									
数量合计 TOTAL PIECES										重量合计 (吨) TOTAL MT									
3										22.344									
(客户有特殊要求按客户要求执行) 正火温度:860-910°C. 正火时间:1.5-2.5 min/mm. NORMALIZED AT 860-910°C. SPECIFIC TIME 1.5-2.5 min/mm										外观及尺寸 ACCEPTABLE VISUAL AND DIMENSIONS									
备注 REMARKS										合格 PASS									
注释 NOTES										合格 PASS									



(1) 分析区分 ANALYSIS: L=冶炼分析 LADLE ANALYSIS. P=成品分析 PRODUCT ANALYSIS. (2) 交货状态 STATE OF DELIVERY: N=正火 NORMALIZED (3) 试验区分 SAMPLING POSITION: B=尾部 BOTTOM. H=头部 TOP. A=任意 ANY. (4) 位置方向 LOCATION AND ORIENTATION: S=表面 SURFACE. C=横截面 Cross Section. T=纵向 TRANS. D=45°. L=纵向 LONGI. Z=厚度方向 THROUGH-THICK. (5) 弯曲 BEND: 按产品标准进行试验. TESTED ACC TO PRODUCT CRITERION. 无要求时, 弯曲试验结果不作交货条件. BENDING TEST IS NOT AS THE CONDITION OF SUPPLY WHERE NOT REQUIRED. (6) 试样尺寸 SPECIMEN SIZE: A=10*10*55; B=10*7.5*55; C=10*5.0*55; D=10*4*55; E=10*2.5*55; F=10*3.5*55; G=10*3.3*55; H=10*8*55; I=10*6.7*55; J=10*6*55 (7) CEV=0.04Mn/6+(Cr+V+Mo)/5+(Cu+Ni)/15 Com14=Nb+V+Ti Com19=Cr+Ni+Cu+Mo (8) 探伤标准: NB/T47013.3-2023, I级合格

本产品已按上述要求进行制造和检验, 其结果符合要求, 特此证明。(符合 EN 10204 3.1 证书)

WE HEREBY CERTIFY THAT THE MATERIALS DESCRIBED HEREIN HAVE BEEN MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS.

(THE CERTIFICATE IS IN CONFORMITY WITH EN 10204 3.1)

PERSON IN CHARGE OF INSPECTION