	n	p ₁₂	V _a (m/s)	ρ (kg/m³)	Ω _B (2π GHz)
Chalcogenide (As ₂ S ₃)	2.37	0.24	2600	3200	7.7
SiO2	1.45	0.27	5960	2203	10