

# General Product information

## Elastollan® SP 9575 QE ESD

® = registered trademark of BASF Polyurethanes GmbH



### Characteristic:

Polyethylen-Compound with low density (LDPE) and antistatic masterbatch, basic Thermoplastic Polyurethane for IDP.

Compound for film extrusion

Property	Unit	Value	Test method according to
Tensile strength	MPa	12	DIN 53504-S2
Elongation at break	%	50	DIN 53504-S2
Volume resistivity	GigaOhm*cm	80	DIN EN IEC 62631-3-1
Yellowness index		12	ASTM E313E-05
Color		natural	-

These are general guidance data. No statement regarding specific properties. All supplies are subject to detailed specifications to be agreed-up in each individual case and containing, among others, the tolerances to be specified therein.

### Drying:

Elastollan® SP 9575 QE ESD is hygroscopic.

The water content of the granules should not exceed 0,05%.

### Storage and Processing:

In cool and dry storage and in the original, undamaged and sealed containers, the products are processable for at least 6 months from delivery date. Thereafter, we do not give any warranty or guarantee regarding the processability and/or shelf life of the products. Warranties regarding buyer's rights in case of defects remain unaffected hereby.

### Delivery form and packing:

Pellets; the packaging dependent upon grade and agreement.

### Storage:

Elastollan® SP 9575 QE ESD is hygroscopic, therefore storage in dry conditions and original packaging is recommended. Once opened bags must be processed immediately.

Material should be pre-dried prior to processing.

### Hazard indication:

No particular hazards known. Please have a look at the Material Safety Data Sheet before handling.

### Waste Disposal:

More detailed information is provided in our country-specific pamphlet and the Material Safety Data Sheet.

### 3 D Printing Applications and hazards:

3 D printing is becoming a popular method for rapid prototyping. Please note that 3-D-printers apply various process mechanisms and it is possible that hazardous vapors and gases might be emitted during the printing process depending on the respective processing conditions. Furthermore, it might be possible that in the process of 3-D-printing, hazardous materials in respect of dermal contacts are used or created. Based on this, we strongly advise against using our product in private 3-D-printing processes. However, as the processes are manifold and not under our control, we regret that BASF Polyurethanes GmbH cannot recommend or give a more detailed indication as to concrete measures to assure a safe handling of our products in 3-D-printing processes. This lies entirely in the responsibility of the respective customers when using or selling our product for 3-D-printing applications.

**Important Information:**

The data contained in this document as well as advice or other support services are based on our current knowledge and experience and are provided according to our best knowledge. In view of many factors that may affect processing and application of our products, this data does not relieve processors from carrying out their own investigations and tests, particularly with regards to the suitability of the goods supplied for the processes and purposes they intend to use them for; neither does this data imply any guarantee of certain properties, or the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, measured values etc. given herein may change without prior notice and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Please notice that this product is not intended for food contact applications.

To determine the suitability of this BASF Polyurethanes GmbH product for certain applications a thorough evaluation by the processor(s), manufacturer(s) and/or distributor(s) is required. National and international laws and regulations have to be considered producing medical devices or consumer articles including but not limited to articles with skin contact or toys.

Where specific regional regulations do not exist, the current legal EU and US requirements as well as globally accepted standards for consumer articles and medical devices should be used as reference.

Please contact BASF Polyurethanes GmbH Sales Office and our Ecology and Product Safety department in case of further questions.

**For additional information please contact our Sales Office:****BASF Polyurethanes GmbH**

Elastogranstraße 60

49448 Lemförde

Telefon +49 (0) 5443/12-3456

Fax +49 (0) 5443/12-2555

E-Mail [elastollan-infopoint@basf.com](mailto:elastollan-infopoint@basf.com)

[www.elastollan.com](http://www.elastollan.com)