

Basonat[®] HI 2000 NG MB

Product description

Basonat[®] HI 2000 NG MB is an aliphatic low viscous isocyanurate for lightfast and weather resistant 2K polyurethane coatings, that complies with the requirements of the REDcert2 certification of sustainable material flows in the chemical industry

Key benefits

- Solvent free
- Low viscosity
- HDI based isocyanate trimer
- High weather resistance
- Good light fastness
- A Biomass Balance product certified according to the TÜV NORD certification standard CMS 71. 100% of the fossil feedstock required for this product is replaced by renewable raw materials (Mass Balance approach).
- By using 1 kg Basonat[®] HI 2000 NG MB (as supplied) app. 1.9 kg of CO₂ savings can be achieved equivalent to app. 1.2 kg of crude oil

Chemical nature

Isocyanurate based on Hexamethylenediisocyanate (HDI)

Properties

Physical form

Transparent, low viscous liquid

Technical data

(not supply specification)

NCO content	DIN EN ISO 11909	22.5-23.5 %
NCO equivalent weight		~ 182
Viscosity at 23 °C (73 °F) D = 1,000 s ⁻¹	DIN EN ISO 3219	900-1,500 mPa s
Platin cobalt color number (Hazen)	DIN EN ISO 6271	≤ 40
HDI content	DIN EN ISO 10283	< 0.1 %

The NCO equivalent weight indicates the amount of Basonat[®] polyisocyanate as supplied containing 1 Mol of active NCO.

Application

Basonat® HI 2000 NG MB is a low viscous, solvent free isocyanurate trimer, that complies with the requirements of the REDcert2 certification of sustainable material flows in the chemical industry.

Basonat® HI 2000 NG MB shows excellent color drift in refinish hardener formulations.

Combined with conventional acrylic resins, a solid content approx. 3% higher than with Basonat® HI 100 NG MB can be achieved. Using high-solids binders such as Joncryl® polyol grades allow the solids content to be increased even further.

Basonat® HI 2000 NG MB allows a broad choice of solvents. For instance, when less volatile solvents would retard drying excessively, like in furniture coatings, highly volatile solvents can be chosen.

Basonat® HI grades are used to formulate particularly lightfast and weather-resistant coatings.

Basonat® HI polyisocyanates are used to crosslink most hydroxy group containing resins e.g., acrylate resins like the Joncryl® polyols and hydroxy polyesters like the hyperbranched Basonol® HPE polyesters. Sufficient compatibility with polyester resins containing hydroxyl groups is not always given.

Formulation guideline

Basonat® HI polyisocyanates can be diluted with esters (e.g. butyl acetate), ketones (e.g. methyl ethyl ketone), glycolether acetates (e.g. methoxypropyl acetate) or with aromatic hydrocarbons (e.g. Solvesso® 100, xylene).

If Basonat® HI polyisocyanates are diluted to a polyisocyanate fraction of less than 40%, turbidity, flocculation and/or sedimentation may occur during storage. Storage trials should always be carried out.

Results from long-term weathering tests show, that in most cases gloss retention is better with isocyanurates than with polyisocyanates based on biurets of hexamethylene diisocyanate (Basonat® HB grades). In addition, due to the low viscosity the solid content can be increased when Basonat® HI grades are used instead of Basonat® HB grades.

The theoretical equivalent amount of polyisocyanate required for crosslinking is computed using this formula:

$$\frac{0.075 \times [\text{OH value}] \times [\text{non volatile fraction of OH component}]}{[\text{NCO}]}$$

Example: Joncryl® 507

OH value [mg KOH/g polyol on solids]	140
Non-volatile fraction (nvf) [%]	80
Basonat® HI 2000 NG MB, NCO content [%]	23

Dosage rate for 100 g Joncryl® 507 as supplied is 36.5 g of Basonat® HI 2000 NG MB.

Solvents, pigments, or extenders etc. used, should be free from compounds containing active hydrogen groups e.g., water, alcohols, or amines.

A water content of less than 500 ppm in solvents and binders is recommended in 2K polyurethane lacquers.

Storage

Basonat® HI 2000 NG MB is sensitive to moisture. The ideal temperature range for storage is 10-30 °C and under airtight conditions (exclusion of humidity and atmospheric oxygen).

Containers should be flushed with nitrogen before resealing.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

®1 = registered trademark of Exxon Mobil Corporation

BASF SE

Resins & Additives Europe

67056 Ludwigshafen, Germany

www.basf.com/resins