Technical Information

Rheovis® PU 1250



general

- polyurethane-based associative thickener
- non-ionic, medium pseudoplastic rheology modifier for water-based coatings
- thickening is pHindependent
- improved flow and gloss
- increased hiding power
- · wash and scrub resistances
- outstanding spatter resistance during roller application

chemical nature

polyurethane polymer in water / butyldiglycol

Properties

physical form

opaque yellowish liquid

storage

Rheovis[®] PU 1250 should be stored in tightly closed containers. The packed product is not damaged by low temperatures or by frost. If stored at low temperatures precipitation or gelatinization of the product is possible. This process is reversible. Please heat product to room temperature and stir well before use.

typical properties

| solvent | water / butyl diglycol |
|------------------------|---------------------------|
| density (25°C) | ~ 1.065 g/cm ³ |
| solid content | ~ 40% |
| viscosity (25°C) | ~ 3,500 mPa·s |
| pH value (2% in water) | ~ 7 |
| | |

Application

Rheovis[®] PU 1250 is suitable for thickening and modification of the flow properties of water-based polymers (e.g. acrylic polymers, vinyl acetate homopolymers, PVAc-VC copolymers, polyurethanes, amineneutralized and emulsified systems).

Because of its low viscosity, Rheovis[®] PU 1250 can be used as supplied. However, it can be diluted with water-soluble co-solvents (e.g. butyl glycol or 1,2-propylene glycol).

recommended concentrations

A dosage of 0.2 - 2.0% calculated on total formulation is recommended.

December 2016 page 2 of 2 Rheovis® PU 1250

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd

45/F, Jardine House No. 1 Connaught Place Central Hong Kong

China

formulation-additives-asia@basf.com

Europe BASF SE

Formulation Additives 67056 Ludwigshafen

Germany

formulation-additives-europe@basf.com

North America BASF Corporation 11501 Steele Creek Road Charlotte, NC 28273

USA

formulation-additives-nafta@basf.com

South America BASF S.A

Rochaverá - Crystal Tower Av. das Naçoes Unidas, 14.171 Morumbi - São Paulo-SP

Brazil

formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Rheovis PU 1250: Rheovis PU 1250, Rheovis PU 1250 NC.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

 $^{^{\}text{®}}$ = registered trademark, $^{\text{TM}}$ = trademark of BASF Group, unless otherwise noted