

Joncryl® 922

Product Description	Joncryl® 922 is a fast-curing acrylic polyol for high solids polyurethane coating applications
Key Features & Benefits	<ul style="list-style-type: none">- Very low VOC- Fast dry time- Utility as a modifier- Supplied in n-Butyl acetate
Chemical Composition	Acrylic polyol

Properties

Typical Properties

Appearance	clear liquid
Non-volatile at 150°C (0.5g, 60 minutes)	~ 80%
Hydroxyl number of solids	~ 140
Viscosity at 25.0 ± 0.5°C (Brookfield #4 LV, 30 rpm, 30 seconds)	3,400 – 7,400 cP
Density at 20°C	~ 1.05 g/cm³ (8.73 lbs/gal)
Equivalent weight as supplied, of solids	~ 500, 400
Tg	~ -7°C
Solvent	n-Butyl acetate

* These typical values should not be interpreted as specifications.

Applications

Joncryl® 922 is an innovative acrylic oligomer for high solids polyurethane coatings. It employs a novel technology, which makes this polyol more reactive with isocyanate crosslinking agents. The result is the ability to formulate fast drying urethane coatings with quick dry times and a practical pot life. High solids coatings for maintenance, transportation, and other applications can be formulated from 2.3 to 3.8 pounds per gallon of VOC.

Joncryl® 922 is supplied in n-Butyl acetate for use in areas where odor is a concern. The Joncryl® 922 is also available in MAK as Joncryl® 920. Joncryl® 922 should be considered as a candidate for high performance, maintenance, and transportation coatings as a replacement for conventional solids urethane finishes. More information can be found in the Joncryl® 920 technical data sheet.

Joncryl® 922 is recommended for applications such as:

- Interior/exterior general metal coating applications
- Automotive refinish coating applications

Formulation Guidelines

Crosslinker Selection – For maximum gloss retention properties, aliphatic isocyanates are recommended. The isocyanurate (trimer) or biuret versions of hexamethylene diisocyanate can be used. The trimer version may give better gloss retention and reactivity. A ratio of 1.05:1 of isocyanate to hydroxyl is normally recommended in the industry. However, a ratio of 1:1 of isocyanate to hydroxyl is more economical and does not sacrifice performance properties.

Solvent Selection – Because the hydroxyl functionality of alcohols and glycol ethers can react with isocyanates, their use should be avoided. Urethane-grade solvents should be used when available. Ketone solvents will give the best viscosity/VOC due to a combination of good solvency and low density. Esters generally provide the next best viscosity/VOC, but do not provide as low of a viscosity/VOC as the ketones due to their higher density. Generally, the lower the molecular weight of the solvent within the family, the lower the viscosity/VOC that is obtainable. Aromatics such as xylene and toluene provide good solvency and can be readily used in combination with the more polar solvents. Glycol ether acetates can be used but normally do not provide as low viscosity/VOC. PM acetate exhibits film retention characteristics.

Catalysis – Due to the increased reactivity of Joncryl® 922, a catalyst is not normally required. If additional speed of cure is desired, typical urethane catalysts such as dibutyltin dilaurate can be utilized. If required, catalysis with 0.005% dibutyltin dilaurate on total binder solids is normally recommended. Higher catalyst levels will result in shorter pot lives and faster cure rates. Other catalysts such as zinc octoate and other metallic soaps can also be used.

Additives – Efka® FL 3670 results in excellent flow and leveling. If a dispersant is necessary, Lecithin or Disparlon¹ KS-273N is recommended. For higher film build, thixotropes such as bentonite clays, fumed silicas, or organic additives such as Thixatrol² can be used.

Starting Point Formulation

The following starting point formulation is recommended for an initial evaluation of Joncryl® 922. Additional optimization of the formulation may be required to achieve desired results for specific applications.

Joncryl® 922 GLOSS WHITE TOPCOAT, Formula #384-B

Part A	Pounds	Gallons
Joncryl® 922	212.10	24.10
Efka® FL 3670	2.45	0.30
n-Butyl acetate	25.00	3.40
Add while mixing:		
Ti-Pure ³ R-960	333.00	10.30
Disperse to 6 – 7 Hegman, then add:		
Joncryl® 922	188.80	21.50
n-Butyl acetate	175.70	23.90
Subtotal	937.05	83.50
Part B		
Basonat® HI 100 NG	160.80	16.50
Total	1,097.85	100.00

Formulation Attributes

Solids	74.3% by wt, 62.0% by volume
Viscosity	120 cP
PVC	16.7%
Pigment:Binder ratio	0.68:1
NCO:OH ratio	1.05:1
VOC (calculated)	2.8 lbs/gal, 338 g/l

¹Registered trademark of King Industries, Inc.

²Registered trademark of Elementis Specialties, Inc.

³Registered trademark of The Chemours Company.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of personal protective equipment.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl® 922.

Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

Joncryn, Efka, and Basonat are registered trademark of BASF Group.

© BASF Corporation, 2023



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins

11501 Steele Creek Road

Charlotte, North Carolina 28273

Phone: (800) 251 – 0612

Email: CustCare-Charlotte@basf.com

www.basf.us/dpsolutions