# **Industrial Coatings**

**Technical Data Sheet** 

# Joncryl® RPD 950-B Polyol



Product Description Joncryl® RPD 950-B is a rapid property development (RPD) acrylic polyol for polyurethane

coating applications.

Key Features & Benefits - Balance of early hardness, fast cure, and pot life

- Exceptional flow and leveling properties

- Early buffability

- Superior clarity and DOI

- Excellent gloss

- Excellent exterior durability

- Very low in-can color

- Low VOC capability

Chemical Composition RPD acrylic polyol

Typical Characteristics

## **Properties**

Typical Properties Appearance clear liquid Non-volatiles (0.5q, 60 minutes, 110°C) ~ 61.0 %

Hydroxyl number ~ 110 mg KOH/g

Viscosity at 25.0°C

Density at 25°C

(Brookfield #4LV, 30 rpm, 30 seconds) 1,000 – 8,000 cps

Equivalent weight as supplied, on solids
Tg
27°C (81°F)
Solvent
n-Butyl Acetate

These typical values should not be interpreted as specifications.

# **Applications**

Joncryl® RPD 950-B is a specialty acrylic polyol with rapid property development for solventborne 2K polyurethane systems in automotive refinish and general industrial applications. This polyol, when crosslinked with either Basonat® HI 100 or HI 190 B/S aliphatic polyisocyanate, provides fast cure with early hardness development and a long pot life. Joncryl® RPD 950-B offers early buffability for automotive refinish applications.

8.51 lbs/gal

Joncryl® RPD 950-B is recommended for applications such as:

- Interior/exterior automotive refinish applications
- Interior/exterior refinish primer surfacer
- Interior/exterior general metal coating applications
- Interior/exterior plastic coatings to polycarbonate and other plastics

May 2017 Rev 3 Page 1 of 2

# Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl® RPD 950-B.

### **Important**

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Joncryl and Basonat are registered trademarks of BASF Group.

© BASF Corporation, 2017



BASF Corporation is fully committed to the Responsible Care<sup>®</sup> initiative in the USA, Canada, and Mexico. For more information on Responsible Care<sup>®</sup> go to: U.S.: www.basf.us/responsiblecare\_usa Canada: www.basf.us/responsiblecare\_canada

Canada: www.basf.us/responsiblecare\_canada
México: www.basf.us/responsiblecare\_mexico

#### **U.S & Canada**

BASF Corporation 24710 W Eleven Mile Road Southfield, MI 48034 ph: 1(800) 231-7868 fax:1(800) 392-7429

Email: DispersionsPigmentsCC@basf.com

Email: edtech-info@basf.com www.basf.us/dpsolutions

#### **Mexico**

BASF Mexicana, S.A. de C.V. Av. Insurgentes Sur # 975 Col. Ciudad de los Deportes C.P. 03710 Mexico, D.F.

Phone: (52-55) 5325-2756 Fax: (52-55) 5723-3011

May 2017 Rev 3 Page 2 of 2