Palatinol® 810TM-I

(Stabilized with 0.1 % 1,1,3-Tris(2-methyl-4-hydroxy-5-tert-butylphenyl)butane antioxidant)

Palatinol® 810TM-I is a primary plasticizer for polyvinyl chloride resins and copolymers. It offers a unique combination of easy processability, a high degree of permanence and good compatibility.

Chemical Nature

8-10 Linear trimellitate

BASF Registered Name

Palatinol® 810TM-I

CAS No.

68130-50-7 (U.S. & Canada)
90218-76-1 (other regions)

Average Molecular Weight

591

Molecular Structure



where R, R' and R'' can be C_6H_{13}, C_8H_{17} or $C_{10}H_{21}$

Product Specifications

	Value	Test Method
Specific gravity @ 25°/25 °C	0.970 - 0.978	ASTM D-4052
Ester content, % by weight (minimum)	99.0	ASTM D-3465
Acid Number, mg KOH/g (maximum)	0.1	ASTM D-1045
Water, % by weight (maximum)	0.1	ASTM E-1064
Color, Pt-Co Units (APHA, maximum)	100	ASTM D-5386
Suspended Matter	COLSFFM*	visual

*Clear Oily Liquid Substantially Free of Foreign Material

Typical Physical Properties

The following data were measured in the BASF Corp. laboratory. They do not represent any legally binding guarantee of properties for our sales product.

	Value
Pour point, °C	-44
Flash point (COC), °C	266
Odor	mild characteristic
Surface Tension, mN/m	31.6
Solution Temperature, °C	154
Plastisol Gelation Temperature, °C	159
Vapor Pressure @ 20 °C, mbar	< 0.01
Solubility @ 25 °C in water, mg/L	< 0.01
Refractive Index $^{\eta}D20$	1.484

Viscosity & Density Data

Temperature (°C)	Dynamic viscosity (cP)	Density (g/cm³)
-20	3,066	1.004
-10	1,168	0.996
0	515	0.989
10	253	0.981
20	137	0.974
40	49.7	0.963
60	22.6	0.946
80	12.1	0.931

Description

Palatinol® 810TM-I, 6-8-10 Linear Trimellitate (8-10 rich), is a primary plasticizer for polyvinyl chloride resins and copolymers. When compared to TOTM and TINTM, formulations made with Palatinol® 810TM-I exhibit superior low temperature flexibility and resistance to oxidative degradation at high temperatures. This trimellitate offers a unique combination of easy processability, a high degree of permanence and good compatibility.

Palatinol® 810TM-I is stabilized with 0.1% 1,1,3-Tris(2-methyl-4–hydroxy–5–tert-butylphenyl)butane.

Applications

Palatinol® 810TM-I is suggested for such applications as wire and cable insulation, refrigerator gaskets, where lacquer mar resistance is a factor, and very low fog automotive components.

Palatinol® 810TM-I is stabilized for electrical applications and where otherwise required.

Safety

Palatinol® 810TM-I does not require special handling. Handle in accordance with good industrial hygiene and safety practices. Avoid eye contact by wearing personal protective equipment. If eye contact occurs, wash with flowing water and contact physician.

Avoid repeated or prolonged skin contact. Avoid breathing vapors by providing adequate ventilation.

Always refer to the Safety Data Sheet (SDS) for detailed information on safety.

Storage and Handling

Palatinol® 810TM-I can be stored for one year at temperatures below 40°C, if moisture is excluded.

Packaging

Palatinol® 810TM-I is available in bulk, tank trucks or rail cars.

Contact Information

Marketing
BASF Corporation
11750 Katy Freeway, Suite 120
Houston, TX 77079, USA

Technical Support
BASF Corporation
4403 La Porte Highway 225
Pasadena, TX, 77501, USA

E-mail: plasticizers@basf.com

Visit us online at
http://www.plasticizers.basf.com

Note

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.