

Acronal[®] 296 D na

Chemical Nature

Aqueous styrene-acrylate copolymer dispersion for the manufacture of building adhesives and coatings

Properties

Typical Properties

Solids content	%	49.0 – 51.0
pH		7.5 – 8.5
Viscosity at 23 °C	mPa s	6000 – 8500
(Brookfield RV and Helipath Stand, Spindle TA, at 20 rpm)		

Other properties of the dispersion

Density	lbs/gal g/cm ³	ca. 8.68 ca. 1.04
Film-forming temperature	°F °C	ca. 68 min. ca. 20 min.
Dispersion type		anionic
Plasticizer content		free from plasticizer
Filler/pigment acceptance		very good
Sensitivity to frost	°F °C	below 32 below 0

Properties of the film

Density	g/cm ³	ca. 1.08
Appearance	clear, transparent	
Surface		tack free
Flexibility		good
Resistance to aging		good

* These figures should be taken for comparison purposes only. All that can be obtained from it is an idea of the magnitude concerned.

Compatible with

Polymer dispersions

Acronal 296 D na is miscible with many other nonionic and anionic aqueous polymer dispersion grades. Note that dried films of such mixtures often appear cloudy.

Thickeners

Polyacrylic acid-based materials (e.g., Rheovis[®] AS 1125), polyvinyl alcohols, cellulose ethers and others such as Collacral[®] VL and Collacral[®] PU, etc.

Plasticizers

Phthalate ester types (e.g., Palatinol[®]), higher molecular weight glycol ethers (e.g., Plastilit[®] 3060)

Coalescents

Texanol[®], mineral spirits, diethylene glycol monobutyl ether, diethylene glycol monobutyl ether acetate.

Fillers

Amorphous and crystalline calcium carbonate, dolomite, silica flour, fine sand, clay, etc. The good compatibility of Acronal 296 D na with pigments and fillers can be further improved by adding Pigment Disperser A or N alone or in combination with potassium polyphosphate. Compounds can be tinted with water-dispersible inorganic and organic pigment preparations (e.g., Luconyl[®]).

Others

Water-dispersable silanes.

Application

Fields of application

Acronal 296 D na is used as a base material for producing adhesives for a large variety of applications including ceramic tiles, plywood-lumber subfloor, cove-base, and flooring. The product is also used in the production of high-gloss to matt coatings for application on plaster, masonry, fibrous cement, concrete, wood, and other indoor and outdoor substrates. Acronal 296 D na also shows great utility as an impregnating agent, primer, or binder for textured finishes.

Acronal 296 D na is also employed in nonwovens and textile coating applications where it generally is applied by dipping, lick-roll, coating or spraying techniques.

Processing

High-speed forced circulation mixers are used in the production of building adhesives, filler compositions, textured finishes, and surfacing compounds, where a high viscosity and high solids content are desirable. In these applications, the polymer dispersion and auxiliaries are first added to the mixer to prepare a pigment paste of the fillers and pigments.

Coatings are generally produced in high-speed mixers (e.g., dissolvers) by predispersing the filler/pigment mixture, incorporating the auxiliaries, and adding the dispersion as the last component.

It is usually necessary to disperse the fillers and pigments with sufficient wetting and dispersing agents (Pigment Disperser A or N, water-soluble phosphates, etc.) in order to obtain products with adequate storage stability.

The film-forming temperature of Acronal 296 D na can be easily reduced further by adding coalescents; for instance, mineral spirits, diethylene glycol monobutyl ether, diethylene glycol monobutyl ether acetate, butoxyethyl acetate, Texanol®, or mixtures of these materials. Diethylene glycol monobutyl ether and Texanol®, for example, simultaneously prolong the open assembly time.

Lower alcohols and glycols improve the resistance to frost, but generally do not reduce the film-forming temperature.

Although Acronal 296 D na already exhibits high viscosity characteristics, a thickening agent is generally added for adjusting the viscosity of the end product. Polyacrylic acid types (e.g. Rheovis® AS 1125, Collacral® VL, Collacral® PU, cellulose ethers or other mineral thickening agents can be used for this purpose. These products not only increase the yield point, but also impart more or less pronounced pseudoplasticity to the end products.

In common with all dispersions of small particle size, Acronal 296 D na has a tendency to foam, and it is generally necessary to add a conventional defoamer in proportions of 0.3-1%

Products containing Acronal 296 D na should be blended with a preservative in order to protect them from the attack of microorganisms. The suitability of the preservative must be determined by trials and regular inspections.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Acronal 296 D.

Storage

Please refer to the "Handling & Storage of Polymer Dispersions" brochure

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Acronal is a registered trademark of BASF Group.

© BASF Corporation, 2025



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation
11501 Steele Creek Rd

Charlotte, NC 28273

ph: 1(800) 231-7868

fax: 1(800) 392-7429

Email: CustCare-Charlotte@basf.com

Email: edtech-info@basf.com

www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.

Av. Insurgentes Sur # 975

Col. Ciudad de los Deportes

C.P. 03710

Mexico, D.F.

Phone: (52-55) 5325-2756

Fax: (52-55) 5723-3011