

Efka[®] IO 6783

General

Ionic liquid, conductivity promoter

EFKA[®] IO 6783 is a medium active additive for a variety of physically drying and reactive coatings. It is used to adjust antistatic property of coatings and resistivity in liquid formulations to prevent from static charge build-up or dust attraction during and after the drying process.

Chemical nature

Hydroxy functional, ammonium salt

Properties

Physical form

Clear colorless to yellowish liquid

Technical data

(not supply specification)

Purity		> 98 %
Water content	DIN 51777	≤ 0.5 %
Viscosity, dynamic		~ 1,100 mPa.s
Melting point,		- 20 °C
Color (Gardner)	DIN EN 1557	≤ 6
OH-number,		612 mg KOH/g
pH value	DIN 19268	7.5 – 8.3

Application

Formulation

EFKA® IO 6783 is designed for waterbased and solventbased formulations. It accepts incorporation together with other additives into the mill base or at the end of the production process.

For the conductivity adjustment of liquid coatings regular amounts of EFKA® IO 6783 in clear coats and pigmented paints ranges from 0.5- 2.0 % calculated on total paint. Depending on pigments and dispersing agent antistatic additive content may vary because of the interaction with pigment surface; the same could happen with mineral matting agents.

In conventional solventbased and high solid 2K PUR systems – taking the high OH number into account – the formulator should calculate the higher need of polyisocyanate. The effect of hygroscopic nature and residual water content in EFKA® IO 6783 on pot life has to be checked.

Like other low molecular weight binders and plasticizers EFKA® IO 6783 may have a softening effect on the final coating. The additive is capable to build three dimensional structures with reduced softening.

Ionic stabilized polymer dispersions can show rheology effects while/after addition of EFKA® IO 6783. The pre-dilution, addition under stirring and use in combination with emulsifying binders improves the storage stability.

Solubility / Compatibility

EFKA® IO 6783 can be formulated with polymer dispersions, polyester, epoxy and acrylate resins. Compatibility with alkyd resins and nitrocellulose is limited. Formulation with VC-copolymers and very hydrophobic resins is not recommended. Many binder combinations result in turbid but stable emulsions.

Because of numerous resins available in the market the formulator needs to carefully check compatibility and storage properties before use.

EFKA® IO 6783 shows excellent acceptance in hydrophilic solvents and diluents like water, methanol, ethanol, Solvenon® PM, glycol ethers and glycol esters, acetone and propylene carbonate. It is not soluble in hydrocarbons and aromatic solvents. There is limited solubility in blends (e. g. ethanol/xylene 7: 3, propylene carbonate/Solvesso® 100 1: 1).

Storage

EFKA® IO 6783 should be stored at 10-30 °C in its originally sealed containers in a clean and dry environment. If the recommended storage conditions are observed EFKA® IO 6783 has a minimum remaining shelf life of 6 months from date of arrival at customers.

EFKA® IO 6783 is slightly hygroscopic. Therefore keep containers tightly closed and avoid handling at high humidity. If possible, exchange air in opened containers by dried air or nitrogen.

Contacts worldwide

Asia
BASF East Asia Regional Headquarters Limited
36/F, Two Taikoo Place,
Taikoo Place,
979 King's Road,
Quarry Bay, Hong Kong
formulation-additives-asia@basf.com

Europe
BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

North America
BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

South America
BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Efka® IO 6783.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

www.basf.com/formulation-additives