

Tinuvin® 384-2

Product Description


Tinuvin 384-2 is a liquid UV absorber of the hydroxyphenylbenzotriazole class developed for coatings. It's very high thermal stability and environmental permanence makes it suitable for coatings exposed to high bake cycles and/or extreme environmental conditions. It has been designed to fulfill the high performance and durability requirements of automotive and industrial high-quality finishes. Its broad UV absorption allows efficient protection of light sensitive base coats or substrates such as wood and plastics.

Key Features & Benefits

- Versatile hydroxyphenyl-benzotriazole UVA for use solvent based coatings
- Excellent spectral coverage in the UV region
- Excellent photopermanence and thermal stability

Chemical Structure

Tinuvin 384-2 is: 95% Benzenepropanoic acid, 3-(2H-benzotriazol-2-yl)-5-(1, 1-dimethylethyl)-4-hydroxy-, C7-9-branched and linear alkyl esters, 5% 1-methoxy-2-propyl acetate



Properties

Typical Properties

CAS No:	127519-17-9, 108-65-6
Appearance	pale yellow liquid
Molecular weight	451.6
Dynamic Viscosity at 20 °C	cps 3,200
Density at 20 °C	g/cm ³ 1.0718


Miscibility (g/100 g solution) at 20 °C:

butanol	> 30
butylcarbitol	> 30
ethyl glycol acetate	> 30
butyl glycol acetate	> 30
methyl ethyl ketone	> 30
1-methoxypropylacetate-2	> 30
Solvesso 100 ¹	> 30
Solvesso 150 ¹	> 30
n – hexane	> 30
water	< 0.01

¹ trademark of Esso

These typical values should not be interpreted as specifications.

Transmittance Spectrum
(in toluene, cell thickness 1 cm)



Top Line: 0.001% Tinuvin 384-2, corresponds to 0.25% in a 40 μ film
Second Line: 0.002% Tinuvin 384-2, corresponds to 0.50% in a 40 μ film
Third Line: 0.004% Tinuvin 384-2, corresponds to 1.0% in a 40 μ film
Bottom Line: 0.006% Tinuvin 384-2, corresponds to 1.5% in a 40 μ film

Applications

Tinuvin 384-2 is recommended for:

- Automotive coatings
- General industrial applications i.e. coil coatings, wood coatings.

The liquid form of Tinuvin 384-2 provides easy incorporation into solvent borne systems.

The performance provided by Tinuvin 384-2 can be enhanced when used in combination with a HALS stabilizer such as Tinuvin 292, Tinuvin 249 or Tinuvin 123. These combinations improve the durability of clear coats by inhibiting or retarding the occurrence of failures such as gloss reduction, cracking, color change, blistering and delamination. The amount of Tinuvin 384-2 required for optimum performance should be determined in laboratory trials covering a concentration range.

Recommend Concentrations	Tinuvin 384-2	1.0 – 3.0 %
	Tinuvin 123, Tinuvin 249 or Tinuvin 292	0.5 – 2.0 %

(concentrations are based on weight percent binder solids)

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measure described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Tinuvin 384-2.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

Tinuvin is a registered trademark of BASF Group.

© BASF Corporation, 2022



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.
For more information on Responsible Care® go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation
Dispersions and Resins
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: CustCare-Charlotte@basf.com
www.basf.us/dpsolutions