

Tinuvin® 479

Product Description	Tinuvin 479 is a hydroxyphenyl-triazine (HPT) UV absorber designed to fulfill the high performance and durability needs for automotive and industrial finishes.
Key Features & Benefits	<ul style="list-style-type: none">- <i>Extremely high extinction coefficient in the UV-B and UV-A range</i>- <i>Low volatility/low migration</i>- <i>Excellent photo-permanence</i>
Chemical Composition	Hydroxyphenyl-triazine UV absorber


Properties

Typical Properties	Appearance	light yellow crystalline powder
	<u>Solubility at 20°C (g/100 g solution):</u>	
	butyldiglycol	2
	butanol	< 1
	butyl acetate	17
	butylglycol acetate	12
	methoxypropl acetate	10
	methoxypropanol	1
	Solvesso® 100 ¹	23
	Solvesso® 150 ¹	10
	water	< 0.01

¹ registered trademark of Esso

These typical values should not be interpreted as specifications.

UV Transmittance Spectrum
in chloroform, cell thickness: 1 cm



Line one: 0.001% Tinuvin 479, corresponds to 0.25% in a 40 µm film
Line two: 0.002% Tinuvin 479, corresponds to 0.50% in a 40 µm film
Line three: 0.003% Tinuvin 479, corresponds to 0.75% in a 40 µm film
Line four: 0.004% Tinuvin 479, corresponds to 1.0% in a 40 µm film
Line five: 0.006% Tinuvin 479, corresponds to 1.5% in a 40 µm film

Applications

Tinuvin 479 is an hydroxyphenyl-triazine UV absorber that provides excellent performance in coatings due to:

- Extremely high extinction coefficient
- Very high photostability for long life performance
- Very high thermal stability and performance for coatings exposed to high bake cycles and / extreme environmental conditions
- Very low volatility
- Excellent performance in thin film applications
- Ideal spectral coverage in combination with other UV absorbers

Tinuvin 479 has been developed as an interaction-free UV absorber to be used in amine and / or metal catalyzed coating systems or in coatings applied on base coats containing such catalysts.

Its high extinction coefficient allows the formulation of coatings with reduced UV absorber levels and / or thin film applications. Combinations especially with other HPT UV absorbers and the newest generation photoinitiators makes it an excellent choice for UV curable coatings.

Tinuvin 479 is recommended for automotive OEM and refinish systems, UV cured coatings, and industrial finishes where long life performance is essential. Due to the high extinction coefficient and superior photostability, applications specifically include thin film applications. Depending on the application, the spectral coverage can be further broadened through combinations with other UV absorbers of the hydroxyphenyl-triazine or hydroxyphenyl-benzotriazole class such as Tinuvin 400 or Tinuvin 928.

The protective effects of Tinuvin 479 can be enhanced when used in combination with hindered amine light stabilizers (HALS) such as Tinuvin 123, Tinuvin 292, or Tinuvin 152. These combinations provide best protection against gloss reduction, cracking, blistering, delamination, and color change. The light stabilizers may be added to clear coats, base coats, or solid shades.

The amount of Tinuvin 479 required for optimum performance should be determined in laboratory trials covering a concentration range.

Recommend Concentrations	0.5 – 2 %	Tinuvin 479 (or Tinuvin 479 + Tinuvin 400, weight ratio 1:2, or Tinuvin 479 + Tinuvin 928, weight ratio 1:2)
	+ 0.5 – 2.0 %	Tinuvin 123 or Tinuvin 292 or Tinuvin 152

(concentrations are based on weight percent binder solids)

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measure described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Tinuvin 479.

Storage

Please refer to the “Handling and Storage of Polymer Dispersions” brochure.

Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK. *Tinuvin is a registered trademark of BASF Group.*

© BASF Corporation, 2022



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins

11501 Steele Creek Road

Charlotte, North Carolina 28273

Phone: (800) 251 – 0612

Email: CustCare-Charlotte@basf.com

www.basf.us/dpsolutions