

# Joncryl® 843

<b>Product Description</b>	Joncryl 843 is a solid flake acrylic resin for industrial hybrid powder coating applications.
<b>Key Features &amp; Benefits</b>	<ul style="list-style-type: none"><li>- <b>Chemical resistance</b></li><li>- <b>Hardness</b></li><li>- <b>Ultra low gloss</b></li><li>- <b>Low-cost epoxy acrylic</b></li></ul>
<b>Chemical Composition</b>	Carboxyl functional acrylic resin

## Properties

<b>Typical Properties</b>	Appearance	clear flake
	Molecular weight	~ 6100
	Non-volatile	> 98%
	Acid number (0.3g in 3A alcohol)	~ 204
	Equivalent weight	~ 275
	Softening point (ring and ball)	~ 140°C
	Tg	~ 86°C

\* These typical values should not be interpreted as specifications.

## Application

Joncryl 843 is a highly functional, acrylic resin suitable for reaction with bis-phenol A epoxies to generate epoxy/acrylic hybrids. Joncryl 843 produces ultra-low gloss with exceptional chemical resistance and hardness at an extremely low formulated cost. Specifically, the balance of properties obtainable with this system in a low gloss black coating make it particularly suitable for general industrial application areas not requiring exceptional flexibility or appearance, like automotive underbody and wire screen.

Joncryl 843 is recommended for applications such as:

- Interior/exterior general metal powder coating applications *Compatibility*, outlines best practices

## Starting Point Formulation

The following starting point formulation is recommended for an initial evaluation of Joncryl 843. Additional optimization of the formulation may be required to achieve desired results for specific applications. This starting point formulation demonstrates ultra-low gloss, outstanding corrosion resistance, and excellent chemical resistance. The exceptional low gloss and cost performance balance makes this a unique system for many industrial and automotive applications.

### Joncryl 843 ACRYLIC HYBRID BLACK, Formula 46-2A

Materials	Parts by Weight
Joncryl 843	16.65
Araldite <sup>1</sup> GT 7013	39.90
Modaflow <sup>2</sup> III	1.00
Benzoin	0.50
Actiron <sup>3</sup> NXJ 60	0.25
Raven <sup>4</sup> 5000	0.70
Lanco <sup>5</sup> PP 1362 D	1.00
Barytes	40.00
<b>Total</b>	<b>100.00</b>

### Extrusion Parameters (BUSS PLK46)

Zones 1 (kneading screw temperature)	65°C
Zones 2 (jacket temperature)	115 - 120°C
RPM	200

### Matte Black Coating Performance Properties

Gloss, 20°/60°	2/5
Direct impact resistance	160 in/lbs
Reverse impact resistance	40 in/lbs
Salt spray (1,250 hrs)	
Creep	2 mm
Blisters	None
Adhesion loss	None

<sup>1</sup>Registered trademark of Huntsman Advanced Materials GmbH.

<sup>2</sup>Registered trademark of Allnex.

<sup>3</sup>Registered trademark of Protex International Corporation.

<sup>4</sup>Registered trademark of Birla Carbon.

<sup>5</sup>Trademark of Lubrizol Corporation.

---

## Safety

### General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

### Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl 843

---

## Storage

Please refer to the "Handling and Storage of polymer dispersions" brochure.

---

## Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

*Joncryn* is a registered trademark of BASF Group.

© BASF Corporation, 2023



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.  
For more information on Responsible Care® go to:  
U.S.: [www.basf.us/responsiblecare\\_usa](http://www.basf.us/responsiblecare_usa)  
Canada: [www.basf.us/responsiblecare\\_canada](http://www.basf.us/responsiblecare_canada)  
México: [www.basf.us/responsiblecare\\_mexico](http://www.basf.us/responsiblecare_mexico)

**BASF Corporation**  
Dispersions and Resins  
11501 Steele Creek Road  
Charlotte, North Carolina 28273  
Phone: (800) 251 – 0612  
Email: [CustCare-Charlotte@basf.com](mailto:CustCare-Charlotte@basf.com)  
[www.basf.us/dpsolutions](http://www.basf.us/dpsolutions)