

Styronal[®] NX 4222 X

Binder for coating paper and paperboard designed for coated rotogravure papers.

Chemical Nature

Aqueous dispersion of a Styrene Butadiene copolymer.

Properties

Typical Properties

Solids content	%	49 - 51
Viscosity at 23 °C (Brookfield RV, Spindle #2, at 20 rpm)	cps	500 – 1200
pH		8.5 - 9.5

Other properties of the dispersion

Type of dispersion		anionic
Density	g/cm ³	1.01
Freeze/thaw stability		not stable

Properties of the film

Appearance		clear
Flexible		yes
Surface		tack-free
Glass transition temperature (DSC)	°C	ca. -25

Compatible with

Styronal NX 4222 X is compatible with other substances commonly used in coating colors.

* The above values should not be taken as specification.

Application

Features

Styronal NX 4222 X yields paper coatings providing excellent compressibility and smoothness. Styronal NX 4222 X is ideally suited for application in rotogravure papers.

Processing

The pH value of pigment slurries should be in the neutral-to-alkaline range before Styronal NX 4222 X is added.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Styronal NX 4222 X.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

Styronal is a registered trademark of BASF Group.

© BASF Corporation, 2022



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins

11501 Steele Creek Road

Charlotte, North Carolina 28273

Phone: (800) 251 – 0612

Email: CustCare-Charlotte@basf.com

www.basf.us/dpsolutions