

Rheovis[®] AS 1125

Product description	Rheology modifier
Key benefits	<div><div>■ Efficient, low-shear acrylic thickener (ASE) with pronounced pseudoplastic flow behavior</div><div>■ Excellent thickening efficiency</div><div>■ Prolonged open time</div><div>■ Increased KU-viscosity</div><div>■ Excellent viscosity stability after tinting</div><div>■ Reduced sagging</div><div>■ Reduced syneresis during storage</div></div>
Chemical nature	Aqueous, acrylic polymer emulsion

Properties

Physical form	White liquid (emulsion)		
Technical data (not supply specification)	Solid Content	ISO 3251	~ 25 %
	Viscosity	ISO 2555	<= 10 mPa.s
	pH value	DIN ISO 976	~ 2.8

Application

Rheovis® AS 1125 is an efficient low-shear, acrylic thickener (ASE) with pronounced pseudoplastic flow behavior for many aqueous paint and coating systems.

Formulation guideline

1.0 - 3.5 % on total formulation.

We recommend determining the optimum dosage level for Rheovis® AS 1125 by laboratory trials to achieve the desired performance.

Rheovis® AS 1125 should preferably be added at the final stage of manufacturing of the formulation. The liquid form of Rheovis® AS 1125 makes post addition comfortable. As a positive side effect, post addition offers the flexibility for viscosity adjustment from batch to batch. Provided efficient mixing equipment is available, Rheovis® AS 1125 can be poured directly into the formulation. It should be avoided that the pH of the system falls below 7.5, by addition of alkali, ammonia or other bases. The usage of ammonia as neutralizing agent improves the water resistance property of the dry film.

Storage

Keep container tightly closed and store in a cool, dry place. Protect from temperatures below 5 °C and above 40 °C. If stored at low temperatures, freezing of the product can irreversibly damage the product.

Contacts worldwide

Asia
BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

North America
BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

Europe
BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

South America
BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Rheovis® AS 1125.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

www.basf.com/formulation-additives