

Rheovis[®] AS S130

Product description Rheology modifier

- Key benefits**
- Highly effective low-shear acrylic thickener (ASE) for a wide range of water-based coatings
 - Excellent thickening efficiency
 - Reduced sagging, syneresis and easy incorporation
 - Outstanding viscosity stability after tinting
 - Advantageous thixotropic behavior in selected formulations, resulting in a non-stringy flow behavior

Chemical nature Aqueous, acrylic polymer emulsion

Properties

Physical form White liquid (emulsion)

Technical data (not supply specification)	Solid content	ISO 3251, modified	~ 30 %
	Viscosity	BASF method	< 40 mPa.s
	pH value	DIN ISO 976	~ 3.5

Application

Rheovis® AS S130 is the ideal ASE rheology-control additive for water-based coatings. It allows coating formulation with an advantageous thixotropic behavior giving a non-stringy flow behavior which is easy to apply over a wide range of speeds and/or processes. Such formulations are ideally suitable e.g. for airless spray applications.

Rheovis® AS S130 is an alkali swellable emulsion type thickener (ASE). Rheovis® AS S130 gives optimum efficiency in a pH range of 7.5 to 10.5.

As a synthetically derived product, Rheovis® AS S130 is less susceptible to microbiological attack than derivatives of cellulose. Consequently, paint formulators can substantially reduce the level of biocide leading to a broader area of application.

Formulation guideline

1.0 - 3.5 % on total formulation

The amount required for optimum performance should be determined in trials covering a certain concentration range.

Rheovis® AS A130 should preferably be added at the final stage of manufacturing of the formulation. The low-viscous, liquid form of Rheovis® AS 1130 makes post addition comfortable. As a positive side effect, this offers flexibility for viscosity adjustment from batch to batch. Provided efficient mixing equipment is available, Rheovis® AS S130 can be poured directly into the mix. Should at any time the pH of the final system drop below 7.5, then additional alkali, ammonium or other base is necessary to reactivate the thickening mechanism. Use of volatile alkali (e.g. ammonia) as neutralizing agent improves the water resistance property of the dry film.

Storage

If the product is in contact with atmospheric conditions, a skin will be formed. Keep container tightly closed and store in a cool, dry place. Protect from temperatures below 5 °C and above 40 °C. If stored at low temperatures, freezing of the product can irreversibly damage the product.

Contacts worldwide

Asia
BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

North America
BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

Europe
BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

South America
BASF S.A.
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Rheovis® AS S130.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

www.basf.com/formulation-additives