

# Dispex® Ultra PX 4275

General	Dispex® Ultra PX 4575 should be incorporated into the mill base before adding the pigments.		
	■	Recommended for highly loaded pigment pastes	
	■	Outstanding flow properties	
	■	Low foaming tendency	
	■	Suitable for air and oven dried coatings	
	■	No negative influence on pot-life of aqueous 2 pack PUR coatings and on corrosion resistance	
Chemical nature	Hydrophilic block-copolymer in water		

## Properties

Physical form	Viscous liquid		
Technical data (not supply specification)	Solid content	DIN EN ISO 3251 (2h at 110 °C)	36.5 – 38.5 %
	Density	BASF method (25 °C)	1.050 – 1.070 g/cm³

Application

Dispex® Ultra PX 4275 is an excellent wetting and dispersing agent for aqueous, binder and solvent-free pigment pastes.

By using Dispex® Ultra PX 4275 an optimum pigment stabilization can be achieved, this also applies to highly loaded pigment pastes. It also gives outstanding flow properties to these systems.

Dispex® Ultra PX 4275 is suitable as wetting and dispersing agent for high quality aqueous coatings based on different binders especially emulsions and dispersions.

Dispex® Ultra PX 4275 has excellent wetting properties to both inorganic and organic pigments and high gloss levels and color strength are easily achieved. Excellent rub-out properties even with critical pigment combinations can be obtained.

Recommended concentrations

Typical dosage of Dispex® Ultra PX 4275 in top coats is 0.5 - 2.5% added to mill base. Recommended dosage for pigment pastes (active substance calculated on pigment) is as follows:

TiO2	5 - 8%
Inorganic pigments	6 - 15%
organic pigments	10 - 30%
Carbon black	40 - 100%

Storage

The product should be protected from frost and stored in a cool dry place (0 – 45 °C).

Contacts worldwide

Asia  
BASF East Asia Regional Headquarters Limited  
36/F, Two Taikoo Place,  
Taikoo Place,  
979 King's Road,  
Quarry Bay, Hong Kong  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)

Europe  
BASF SE  
Formulation Additives  
67056 Ludwigshafen  
Germany  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)

North America  
BASF Corporation  
11501 Steele Creek Road  
Charlotte, NC 28273  
USA  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)

South America  
BASF S.A  
Rochaverá - Crystal Tower  
Av. das Nações Unidas, 14.171  
Morumbi - São Paulo-SP  
Brazil  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)

Validity

This Technical Data Sheet is valid for all versions of the Dispex® Ultra PX 4275.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product foDispex® Ultra PX 4575 should be incorporated into the mill base before adding the pigments.r a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark  
™ = Trademark of the BASF Group, unless otherwise noted